

Bio-corrosion detection by sulphur isotopic fractionation measurements using nanoSIMS

Sophie Grousset, Florence F. Mercier-Bion, A. Dauzères, D. Crusset, V Deydier, Y. Linard, S. Mostefaoui, Delphine D. Neff, Philippe Dillmann

► To cite this version:

Sophie Grousset, Florence F. Mercier-Bion, A. Dauzères, D. Crusset, V Deydier, et al.. Bio-corrosion detection by sulphur isotopic fractionation measurements using nanoSIMS. Goldschmidt 2017, Aug 2017, Paris, France. cea-02331853

HAL Id: cea-02331853 https://cea.hal.science/cea-02331853

Submitted on 24 Oct 2019

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers. L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

Bio-corrosion detection by sulphur isotopic fractionation measurements using nanoSIMS

S. GROUSSET¹²³, F. MERCIER^{1*}, , A. DAUZERES², D. CRUSSET³, V. DEYDIER³, Y. LINARD³, S. MOSTEFAOUI⁵, P. DILLMANN¹, D. NEFF¹

¹LAPA-IRAMAT, NIMBE, CEA, CNRS, CEA Saclay, 91191 Gif-sur-Yvette, France (*presenting author, florence.mercier@cea.fr)

²IRSN, PRP-DGE/SRTG/LETIS, B.P.17, 92262 Fontenayaux-Roses, France (<u>alexandre.dauzeres@irsn.fr</u>)

³Andra, 1-7 rue Jean Monnet, 92298 Châtenay-Malabry, France (<u>didier.crusset@andra.fr</u>)

⁴IMPMC-COSMO, MNHN, 75005 Paris, France (<u>smail@mnhn.fr</u>)

The presence of Sulphate-Reducing Bacteria (SRB) may influence the corrosion rate of ferrous objects by inducing iron sulphides precipitation. The same phases are formed by biotic or abiotic ways. Yet, biotic iron sulphides are supposed to be depleted in heavy isotopes of sulphur relative to the starting sulphates [1]. So, sulphur isotopic composition analyses enable to determine the (a-)biotic origin of the iron sulfides. Previously, a single study [2] devoted to corrosion issues had used the sulphur isotopic composition to determine the origin of sulphides compounds formed on Cu/Ni steel. However, the sulphur isotopic fractionation was obtained by global mass spectrometry from the precipitation into BaSO₄ of the remaining sulphates of the corrosion experiment. This method is not adapted to the iron sulphides formed in field samples, presents as strips of some micrometers size [3].

To fill this analytical gap, in the study presented here, nanoSIMS (nanoscale Secondary Ion Mass Spectrometry) is used to determine the local sulphur isotopic composition of the iron sulphides within the corrosion product layers of two kinds of field samples: a short term system consisting of a steel coupon buried for 24 months in the Andra (French National Radioactive Waste Management Agency) Underground Research Laboratory devoted to research on the geological disposal of radioactive waste at Bure (Grand Est, France); and long term systems composed of iron nails buried in the water-saturated soil of the archeological site of Glinet (Normandie, France) during around 500 years. Thus, thanks to the methodology developed the iron sulphide bio-origin is proved in both corroded samples.

[1] Sim *et al.* (2011) *Science* **333**, 74–77. [2] Little *et al.* (2012) *Biofouling* **6**, 279–288. [3] Grousset *et al.* (2016) *Corros. Sci.* **112**, 264–275.