

#### Effect of cavities induced by ion implantation on rare gases diffusion in uranium dioxide

M. Gerardin, E. Gilabert, D. Horlait, P. Desgardin, G. Carlot, M-F. Barthe

#### ► To cite this version:

M. Gerardin, E. Gilabert, D. Horlait, P. Desgardin, G. Carlot, et al.. Effect of cavities induced by ion implantation on rare gases diffusion in uranium dioxide. SHIM-ICACS - 10th International symposium on swift heavy ions in matter & 28th international conference on Atomic collisions in solids, Jul 2018, Caen, France. cea-02338620

#### HAL Id: cea-02338620 https://cea.hal.science/cea-02338620v1

Submitted on 21 Feb2020

**HAL** is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers. L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

# Effect of cavities induced by ion implantation on rare gases diffusion in uranium dioxide

M. Gerardin<sup>1\*</sup>, E. Gilabert<sup>2</sup>, D. Horlait<sup>2</sup>, P. Desgardin<sup>3</sup>, G. Carlot<sup>1</sup>, M-F. Barthe<sup>3</sup>

<sup>1</sup> CEA/DEN/DEC (Saint Paul Lez Durance, France) <sup>2</sup> CENBG, CNRS/IN2P3 (Gradignan, France) <sup>3</sup> CEMHTI, CNRS/UPR3079 (Orléans, France)

DE LA RECHERCHE À L'INDUSTRIE Cea den Cemht \* CENBG **INSPYRE** 



chemical properties limiting fuel life time in reactor

# **Objectives**

Thermal desorption

measurements

Gas release fraction

- Improve the modelling of fission gas thermal diffusion mechanisms to better predict UO<sub>2</sub> fuel behaviour under irradiation
- Study the interaction between gas and defect induced by irradiation



## Literature

### **Diffusion coefficient dependance**

- Stoichiometry of the sample
- Burn up (fission.m<sup>-3</sup>)



- $\succ$  Gases are trapped in UO<sub>2</sub> for a burn-up > 2.10<sup>22</sup> f.m<sup>-3</sup>
- In which defects ?



23 GWj/tU

[1] Long, Davies and Findlay, AERE-M1251 (1964) [2] Lindner and Matzke, Z. Naturforschung 14a (1959) [3] Miekeley and Felix, JNM 42 (1972)

#### Transmission **Positron annihilation Electron Microscopy** spectroscopy (PAS) (TEM)

**Diffusion model : two populations** 

Second Fick law  $C_i(0,t) = 0$  $\frac{1}{10}$  4.0x10<sup>4</sup> For i = 1 or 2:  $D_{i} \frac{\partial^{2} C_{i}(x,t)}{\partial^{2} x} = \frac{\partial C_{i}(x,t)}{\partial t} \begin{bmatrix} C_{i}(\infty,t) = 0 \\ C_{i}(\infty,t) = 0 \\ C_{1}(x,0) = (1-M) \times C_{SRIM Profile} \begin{bmatrix} 0 \\ 0 \\ 0 \end{bmatrix}^{2} 2.0 \times 10^{4} \end{bmatrix}$ For i = 1 or 2 : M = 0.95  $D_1 = 3.10^{-17} \text{ m}^2.\text{s}^{-1}$  $D_2 = 1.10^{-20} \text{ m}^2.\text{s}^{-1}$  $\Gamma_{\text{final}} = 500 \text{ min}$ 100 Depth (nm)  $(C_1)$ : Gaz concentration mobile with  $D_1 \longrightarrow$  Burst effect **M** : Fraction of 2 populations

 $C_2$ : Gaz concentration mobile with  $D_2 \rightarrow$  Intrinsic diffusion

# • Trapping effect

### 1. Thermal desorption

Diffusion coefficient (D<sub>2</sub>) determined on isotherms obtained at 1300°C for each dose

- $\geq$  D<sub>1</sub> remains constant
- $\geq$  D<sub>2</sub> decreases from
  - 10<sup>13</sup> ions.cm<sup>-2</sup> in polycrystals
  - 10<sup>12</sup> ions.cm<sup>-2</sup> in monocrystals

## **Trapping effect in implanted UO**<sub>2</sub>

 $C_1(x,0) = (1-M) \times C_{SRIM \, Profile}$  $C_2(x,0) = M \times (1 - Fr_{init}) \times C_{SRIM Profile}$  $C_P(x, 0) = M \times Fr_{init} \times C_{SRIM Profile}$ 

**F***rinit* : Fraction of trapped gas atom

Increases with the fluence

## 2. Trapping sites







 $-C_{1}(x,0)$ 

 $- - C_1(x,t)$ 

 $-C_{2}(x,0)$ 

 $- - C_{2}(x,t)$ 

300

200

▲ Xe 1.4e11 (1s - Poly)

Time (min

Simulated with  $D_a = 0$ 

Simulated with  $D_2 \neq 0$ 



Rare gases trapped in cavities induced by irradiation