



HAL
open science

An auto-catalytic mechanism to model the fission gas release between 600°C and 800°C on UO₂ irradiated fuel.

Yves Pontillon, G. Brindelle, G. Baldinozzi, H. Capdevila, L. Desgranges

► **To cite this version:**

Yves Pontillon, G. Brindelle, G. Baldinozzi, H. Capdevila, L. Desgranges. An auto-catalytic mechanism to model the fission gas release between 600°C and 800°C on UO₂ irradiated fuel.. MRS spring 2018, Apr 2018, Phoenix, United States. cea-02339066

HAL Id: cea-02339066

<https://cea.hal.science/cea-02339066v1>

Submitted on 13 Dec 2019

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

DE LA RECHERCHE À L'INDUSTRIE



université
PARIS-SACLAY

ÉCOLE DOCTORALE
INTERFACES
Approches Interdisciplinaires :
Fondements, Applications et Innovation



CentraleSupélec

www.cea.fr

AN AUTO-CATALYTIC MECHANISM TO MODEL THE FISSION GAS RELEASE BETWEEN 600°C AND 800°C ON UO_2 IRRADIATED FUEL.

YVES PONTILLON¹, GUILLAUME BRINDELLE^{1,2}, GIANGUIDO
BALDINOZZI², HÉLÈNE CAPDEVILA¹, LIONEL DESGRANGES¹

¹CEA, DEN/DEC, F-13108 SAINT-PAUL-LEZ-DURANCE, FRANC


²CNRS, SPMS, LRC CARMEN, CENTRALESUPELEC, F-91190 GIF-SUR-

YVETTE, FRANCE

Release of Fission products during a LOCA accident


Loss Of Coolant Accident

Breach in primary circuit



Safety assessment requires the inventory of released Fission Products

Average temperature during a LOCA



Fast heating


Plateau at $T_{max} = 1200^{\circ}\text{C}$

Fast cooling due to reflooding

Measurement of Fission Gas release at CEA Cadarache

LECA-STAR
Hot laboratory

M



Carrier gas and released FPs

Gamma spectrometry
 μ -GC



Carrier gas

Fission Gas Release measured using MERARG

Temperature profile for LOCA :


- first plateau at 300°C
- Ramp 20°C/s
- Plateau at 1200°C



Too fast in MERARG for mechanism decoupling




Understanding temperature profile:
• Ramp 0,2°C/s




Bursts of Fission Gas Release

UO₂ fort taux de combustion : 72 GWj/t



Comes from High Burn-up Structure

J. Noiroot , Y. Pontillon, *JNM 446,163-171, 2014*



- Proposed mechanism:
- Highly pressurized bubbles of HBS release the gas they contain

Up to now no validated mechanism is proposed for the burst at 600-800°C

An analysis of the experimental data set obtained with MERARG in order to evidence some trends :


Correlation between the burst at 600-800°C and experimental parameters ??

Parameters of MERARG data set

➤ From November 2000 up to nowadays more than 200 heat treatments in MERARG

Which ones are relevant?

- Temperature profiles related to LOCA
- First plateau at 300°C and then temperature ramp in inert atmosphere.



14 UO₂

~~20 MOX~~

Experimental conditions:

- Crucible
- Carrier gas
- Ramp up to 300°C



No influence of experimental conditions

Samples characteristics :

BU (GWj/tM)	Storage (d)	1 st burst (%)
76,94	1137	4,8
	2627	6,0
	3317	9,2

no correlation for MOX

Gas release in %

:

5

Nombre de cycles

7

8

0

2

50

taux de combustion (GWj/tM)

60

70

80

12

Strong correlation between FGR and storage duration for UO₂

Gas rel

4

2

0

Storage time in days

N/cm)

0


195

200

What happen during storage duration ?


Storage at low temperature :

- No thermally activated diffusion
- Creation of defects due to self-irradiation
- Defects that can be annealed by heat treatment



Annealing kinetics of self irradiation defects in Pu doped UO_2

Staicu & al., JNM 397, 2010



600-800°C :
Annealing of U vacancies [1][2]



Fission gas release :
A mechanism derived from
autocatalytic of uranium vacancies ?

[1] H. Matzke, *Radiation-Damage in Nuclear-Materials*, Mar. 1992.

[2] H. Labrim & al. Aug. 2007.

A tentative modeling of Fission Gas release in MERARG


Simplified mechanism with 2 steps (Finke-Watzky type)

Formation of nano-clusters in steels

Evolution of nano-particles in colloidal solutions²


Modeling for auto-catalytic kinetics

Brindelle, Numat2016



$$Fr(t) = A_0 \left(1 - \frac{1 + \frac{k_1}{A_0 k_2}}{1 + \frac{k_1}{A_0 k_2} \exp \left[\left(1 + \frac{k_1}{A_0 k_2} \right) A_0 k_2 t \right]} \right)$$

A_0 : available gas capacity for release



$$cumulated\ fraction = \frac{\text{released gas quantity}}{\text{initial gas quantity}}$$


¹M. A. Watzky & al., *Am. Chem. Soc.*, vol. 130, no. 36, pp. 11959–11969, Sep. 2008.

²D. V. Talapin & al., *J. Phys. Chem. B*, vol. 105, no. 49, pp. 12278–12285, Dec. 2001.

Comparison modeling/measurements


$k_{1\text{moy}} = 2,7 \pm 0,11 \cdot 10^{-4} \text{ min}^{-1}$

$k_{2\text{moy}} = 2,97 \pm 0,07 \text{ min}^{-1}$



Conclusion, storage time induces:

- An increase of gas release at 600-800°C burst that appears in the modeling by the increase of A_0 , gas quantity available for release.



Conclusion

The quantity of gas release during the burst at 600-800°C depends on storage time.

The release mechanism could be due to the annealing of self-irradiation defects that were produced during storage. A kinetic model is proposed to describe this release mechanism.

The storage time is a first order parameter for gas release experiment that needs to be taken into account.

Thank You for your attention

Commissariat à l'énergie atomique et aux énergies alternatives
Centre de Cadarache | 13108 Saint-Paul lez Durance Cedex

DEN
DEC
SA3E

Etablissement public à caractère industriel et commercial | R.C.S Paris B 775 685 019