



**HAL**  
open science

## Magnetron-sputtered Ta<sub>3</sub>N<sub>5</sub> thin films for water photoelectrolysis

M. Rudolph, B. Bouchet-Fabre, M.-C Hugon, E. Foy, D. Stanesco, J. Alvarez,  
H. Magnan, Jean-Paul Kleider, T. Minea

► **To cite this version:**

M. Rudolph, B. Bouchet-Fabre, M.-C Hugon, E. Foy, D. Stanesco, et al.. Magnetron-sputtered Ta<sub>3</sub>N<sub>5</sub> thin films for water photoelectrolysis. European Advanced Materials Congress, Aug 2017, Stockholm, Sweden. cea-02340854

**HAL Id: cea-02340854**

**<https://cea.hal.science/cea-02340854>**

Submitted on 31 Oct 2019

**HAL** is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

# magnetron-sputtered Ta<sub>3</sub>N<sub>5</sub> thin films for water photoelectrolysis

M. Rudolph<sup>1,2</sup>, B. Bouchet-Fabre<sup>1</sup>, M.-C. Hugon<sup>2</sup>, E. Foy<sup>1</sup>, D. Stanescu<sup>1</sup>,

J. Alvarez<sup>3</sup>, H. Magnan<sup>1</sup>, J.-P. Kleider<sup>3</sup>, T. Minea<sup>2</sup>

<sup>1</sup> NIMBE, CEA/CNRS, Université Paris-Saclay, 91191 Gif-sur-Yvette, France

<sup>2</sup> LPGP, Univ. Paris-Sud/CNRS, Université Paris-Saclay, 91405 Orsay, France

<sup>3</sup> GeePS, CentraleSupélec, Université Paris-Saclay, 91192 Gif-sur-Yvette, France



\*Corresponding author. Tel: (+33) 630734793; Fax: (+33) 169081213; E-mail: [bribouchet@gmail.com](mailto:bribouchet@gmail.com)

## Abstract

Ta<sub>3</sub>N<sub>5</sub> has aroused interest in the scientific community as a small-band gap semiconductor able to split H<sub>2</sub>O molecules under sunlight illumination (3). Although its band gap of 2.1eV is highly suited (1), its synthesis is difficult. In this work, DC magnetron sputtering is used to successfully deposited thin films of Ta<sub>3</sub>N<sub>5</sub> : the influence of the working gas composition Ar/N<sub>2</sub>/O<sub>2</sub> on the film properties is studied, notably the role of oxygen as a crucial ingredient for the structure. Previous attempts using magnetrons employed RF sputtering and investigated primarily temperature effects (2,4) .

The films were characterized structurally, optically (transmission/reflection spectrophotometry), electrically, chemically and subjected to photocatalytic measurements in 0.1M K<sub>2</sub>SO<sub>4</sub> aqueous solution adjusted to pH=11 by KOH.

We show that variations scale with the O<sub>2</sub> flowrate: from amorphous at high O<sub>2</sub> flowrates, to Ta<sub>3</sub>N<sub>5</sub> crystallization at reduced O<sub>2</sub> flowrate. Photo-spectrometry analyzed with a Tauc-Lorentz oscillator model shows that the band gap scales with the oxygen flowrate, from a metallic behavior to a maximum gap of 2.5 eV. Photocurrent measurements corrected by the conductivity in darkness show an insulating character for all films. Nevertheless the photo-conductivity drops by 9 orders of magnitude with increasing O<sub>2</sub> flowrate to reach minimum values around 10<sup>-9</sup>S/m..

**Keywords:** magnetron sputtering; structural properties; optical gap; oxy-nitride; photoelectrolysis

## Reference

- 1 Bak, T., et al.; Int. J. Hydrogen Energy 27 (2002) 991
- 2 Ishihara, A. et al; Electrochim. Acta 53 (2008) 5442
- 3 Maeda, K., Domen, K.; J. Phys. Chem. C 111 (2007) 7851
- 4 Yokoyama, D., et al. T S F. 519 (2011) 2087