



**HAL**  
open science

## Aging of Solution processed perovskite solar cells

Heejae Lee, Arthur Marronnier, Denis Tondelier, Sandrine Tusseau-Nenez,  
Yvan Bonassieux, Bernard Geffroy

► **To cite this version:**

Heejae Lee, Arthur Marronnier, Denis Tondelier, Sandrine Tusseau-Nenez, Yvan Bonassieux, et al..  
Aging of Solution processed perovskite solar cells. 2èmes journées Pérovskites hybrides (JPH2016),  
May 2016, Rennes, France. cea-02349409

**HAL Id: cea-02349409**

**<https://cea.hal.science/cea-02349409v1>**

Submitted on 5 Nov 2019

**HAL** is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

# Aging of Solution processed perovskite solar cells

Heejae Lee<sup>1</sup>, Arthur Marronnier<sup>1</sup>, Denis Tondelier,<sup>1</sup> Sandrine Tusseau-Nenez<sup>2</sup>,  
Yvan Bonassieux<sup>1</sup> and Bernard Geffroy<sup>1,3</sup>


<sup>1</sup> LPICM, CNRS, Ecole Polytechnique, Université Paris-Saclay, 91128 Palaiseau, France

<sup>2</sup> LPMC, CNRS, Ecole Polytechnique, Université Paris-Saclay, 91128 Palaiseau, France

<sup>3</sup> LICSEN, NIMBE, CEA, CNRS, Université Paris-Saclay, CEA Saclay, 91191 Gif Sur Yvette Cedex, France

heejae.lee@polytechnique.edu

In recent years, perovskite ( $\text{CH}_3\text{NH}_3\text{PbI}_{3-x}\text{Cl}_x$ ) solar cells have been studied steadily due to their potential properties: low-cost processing and possibility to produce large area by low temperature processes. The perovskite film used as light absorber is obtained by solution process and has a crystalline structure. Many different solvents are being developed and gradually adopted for high-performance inorganic-organic hybrid perovskite solar cells. PEDOT:PSS and PC<sub>60</sub>BM are used as hole transport layer (HTL) and electron transport layer (ETL), respectively. The size of active area is 0.28cm<sup>2</sup>. In this study, 9.54% of power conversion efficiency (PCE) is obtained with a saturated current density (Jsc) of 15.03 mA/cm<sup>2</sup>. The degradation of the performance of the solar cell is studied with XRD measurements as well as electrical characterizations. The perovskite solar cell performance decreases with aging time (Table 1 and Figure 1a) and XRD data show the growing of the PbI<sub>2</sub> peak and a decreasing of the CH<sub>3</sub>NH<sub>3</sub>PbI<sub>3</sub> (MAPbI<sub>3</sub>) peak.



**Fig. 1: (a) J-V curve of best performance in 3 days with full device structure and energy band-diagram of solar cells device in this study, (b) XRD data after 0, 6 and 13 days**

After # Day	Jsc (mA/cm <sup>2</sup> )	Voc (V)	FF (%)	PCE (%)	Rs	Rsh
0 day	15.03	0.92	69	9.54	9.52	3130
1 day	12.37	0.87	65	6.93	10.3	250
2days	7.65	0.85	61	3.96	14.5	261

**Table 1: Basic parameters of perovskite solar cells to check degradation in this study**