



HAL
open science

Degradation mechanisms of reinforcement iron rebars in monuments: Time-resolved X-ray microtomography of water percolation in corrosion layers

M Jacot-Guillarmod, A. King, O Rozenbaum, Delphine D. Neff, C. Gervais

► To cite this version:

M Jacot-Guillarmod, A. King, O Rozenbaum, Delphine D. Neff, C. Gervais. Degradation mechanisms of reinforcement iron rebars in monuments: Time-resolved X-ray microtomography of water percolation in corrosion layers. Synchrotron Radiation and Neutrons in Art and Archaeology Conference (SR2A 2016), Sep 2016, Chicago, United States. cea-02349520

HAL Id: cea-02349520

<https://cea.hal.science/cea-02349520v1>

Submitted on 5 Nov 2019

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

O3-Degradation mechanisms of reinforcement iron rebars in monuments: Time-resolved X-ray microtomography of water percolation in corrosion layers

M. J.-Guillarmod¹, A. King², O. Rozenbaum³, D. Neff^{4,5}, C. Gervais¹

¹Bern University of the Arts, CH-3027 Bern, Switzerland

²Synchrotron SOLEIL, F-91192 Gif Sur Yvette, France

³University of Orleans, CNRS, BRGM, ISTO, UMR 7327, F-45060 Orleans, France

⁴LAPA NIMBE SIS2M UMR3299 CEA CNRS, F-91191 Gif Sur Yvette, France

⁵CEA Saclay, IRAMAT CNRS UMR5060, F-91191 Gif Sur Yvette, France

Iron rebars have been used for centuries in stone monuments. Their corrosion seriously endangers the structural integrity of the monument in the long term and thus needs to be appropriately assessed and understood. Corrosion layers are constituted of different iron oxides and oxi-hydroxides, along with a significant porosity which plays a significant role in the corrosion process by allowing transport of electrolytes from outside to the vicinity of the metal core [1]. Previous investigations by X-ray microtomography have shown that this porosity forms a complex and anisotropic network with pores ranging from the micro- to the nano-scale [2].

Here we show that time-resolved X-ray microtomography allows to visualize the flow of water within the corrosion layers, a first step towards the quantification of important transport properties such as permeability and diffusion coefficients. Samples of corroded iron rebars from the cathedral of Metz were cut and embedded into resin to present a cavity on the top of the corroded surface where water mixed with a contrast product was added. X-ray microtomography images of 870nm voxel size were acquired by propagation phase contrast on the PSICHE beamline, with a pink beam of 63keV. After imaging of the dry sample, the contrast solution was added and tomography images were acquired every few minutes, allowing after suitable image processing the 3D time-resolved visualization of water percolation in the corroded layers (Figure 1). We further characterized the process by means of several metrics (chord distribution functions, Betti numbers and diffusion coefficient computations) and could evidence a two-step percolation dynamics and the influence of sub-resolution nanoporosity.




Fig. 1 Water percolation of the porosity over time (blue: immediate, red: 30-35 minutes) in the corrosion layer of an iron rebar from the cathedral of Metz. Red zones show pores not directly connected to the main porosity network, where water percolates only in a second stage.

References

- [1] Demoulin A., Trigance C., Neff D., Foy E., Dillmann P., and L'Hostis V. *Corrosion Science*, 52:3168–3179, 2010.
- [2] Jacot-Guillarmod M., Rozenbaum O., L'Hostis V., Dillmann P., Neff D., and Gervais C., *Journal of Atomic Analytical Spectroscopy*, 30(3):580–587, 2015.