



**HAL**  
open science

## **ZnFe<sub>2</sub>O<sub>4</sub> nanoparticles synthesis by laser pyrolysis: interest as new anode material for lithium-ion batteries**

Samantha Bourrioux, Luyuan Paul Wang, Yann Leconte, Madhavi Srinivasan,  
Zhichuan Xu, Alain Pasturel

### ► To cite this version:

Samantha Bourrioux, Luyuan Paul Wang, Yann Leconte, Madhavi Srinivasan, Zhichuan Xu, et al..  
ZnFe<sub>2</sub>O<sub>4</sub> nanoparticles synthesis by laser pyrolysis: interest as new anode material for lithium-ion  
batteries. Energy Future 2016, Jul 2016, Sydney, Australia. cea-02351515

**HAL Id: cea-02351515**

**<https://cea.hal.science/cea-02351515>**

Submitted on 6 Nov 2019

**HAL** is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

## **ZnFe<sub>2</sub>O<sub>4</sub> nanoparticles synthesis by laser pyrolysis: interest as new anode material for lithium-ion batteries**

*Samantha Bourrioux<sup>1\*</sup>, Luyuan Paul Wang<sup>1,2</sup>, Yann Leconte<sup>1</sup>, Madhavi Srinivasan<sup>2</sup>, Zhichuan J. Xu<sup>2</sup>, Alain Pasturel<sup>3</sup>*

<sup>1</sup>CEA, IRAMIS, NIMBE, CNRS UMR 3685, F- 91191, Gif-sur-Yvette, France

<sup>2</sup>School of Materials Science and Engineering, Nanyang Technological University, Singapore

<sup>3</sup>SIMAP, UMR CNRS 5266, Grenoble INP, BP 75, 38402 Saint-Martin d'Hères, France

*Samantha Bourrioux : Samantha.bourrioux@cea.fr*

The development of portable devices, electric vehicles and renewable energies has motivated research works about energy storage for years. Existing lithium-ion batteries cannot reach sufficient energy density to address the needs for such applications. One of the issues limiting the energy density is the low specific capacity of the graphite anode (372 mAh.g<sup>-1</sup>).

Mixed-transition metal oxides with a spinel structure (AB<sub>2</sub>O<sub>4</sub> – A, B transition metals) appear as a promising solution to replace graphite with a higher theoretical capacity (between 750 and 1000 mAh.g<sup>-1</sup>). Nanostructuration of these compounds was studied to maintain mechanical stability and to enhance lithiation kinetics. ZnFe<sub>2</sub>O<sub>4</sub> is an interesting substitute to graphite as the storage mechanism gives rise to a theoretical capacity of 1001 mAh.g<sup>-1</sup> and among various oxides, ZnFe<sub>2</sub>O<sub>4</sub> is cheap, abundant and non-toxic.

Compared with oxides like Fe<sub>2</sub>O<sub>3</sub>, the combination of two transition metals contributes to lower the working voltage vs. Li/Li<sup>+</sup> (1.5V for ZnFe<sub>2</sub>O<sub>4</sub> vs. 2.1V for Fe<sub>2</sub>O<sub>3</sub>).

ZnFe<sub>2</sub>O<sub>4</sub> nanoparticles were synthesized by laser pyrolysis. In this process, an aerosol containing precursors droplets produced by a nebulizer, is flown into the reactor with a carrier gas. In the reactor, a 10.6 μm-CO<sub>2</sub> laser beam decomposes the precursors to obtain nanopowders which are then collected on a filter. The key advantage of laser pyrolysis is the ability to obtain nanomaterials in large scale with a high purity while controlling the grain size with the appropriate parameters.

Solutions containing Zn(NO<sub>3</sub>)<sub>2</sub>.6H<sub>2</sub>O and Fe(NO<sub>3</sub>)<sub>3</sub>.9H<sub>2</sub>O dissolved in deionized water were used for the synthesis of ZnFe<sub>2</sub>O<sub>4</sub> nanoparticles. Ethylene was used as sensitizer gas to absorb the CO<sub>2</sub> laser and allow the decomposition of the precursors whereas air and argon were tested as carrier gases. Powders of different morphologies and crystallinities were obtained and characterized by XRD, SEM, EDX, HRTEM and XPS. ZnO and Fe<sub>2</sub>O<sub>3</sub> were also synthesized to compare their electrochemical performances with those of ZnFe<sub>2</sub>O<sub>4</sub>. All the results were compared with literature.