DE LA RECHERCHE À L'INDUSTRIE



A combined process for the selective rare earth recovery and separation from used permanent magnets

E. Andreiadis, M. Miguirditchian, V. Haquin, V. Pacary, M. Montuir, L. Diaz, J. Serp, R. Laucournet

CEA, DEN, DRCP RadioChemistry and Processes Department, Marcoule, France

CEA, DRT, LITEN Laboratory for Innovation in New Energy Technologies and Nanomaterials, Grenoble, France



www.cea.fr

REE production, supply risk and applications



- Rare earth elements (REE) = Critical raw materials for European economy ?
- Global REO production 125 000 T/yr
- > Significant price drop in 2015 (excess supply, illegal mining)
- > RE demand growing, especially for magnets (Nd, Dy most critical)
- Production chain concentrated in China (mining, separation, downstream manufacturing, R&D capacity): 85% world REO supply
- All heavy REE production controlled by China
- Currently no European mine in operation (Norra Karr lease cancelled)



- Most NTE applications require pure elements, but REE extracted as a group
- > Earth abundance decreases along the series
- Most abundant elements have few applications

Need to diversify supply sources especially for heavy, critical elements (Dy)

REE recycling: closing the materials loop

Advantages of recycling

- > Target the most critical rare earths and address the balance problem
- > No issues with radioactive elements (235U, 238U, 232Th)
- Lower environmental footprint





Challenges

- Very low recycling rates for REE
- > Insufficient and untargeted **collection** of waste sources (such as WEEE)
- > Difficult recovery of REE-containing fractions (design, coatings, adhesives)
- Difficult separation of individual REE
- > Optimization of re-processing technologies
- Economic incentive

Opportunities

- Competences and expertise of the European recycling industry
- Leveraging on the urban mine
- Economic and environmental impact



Recycling NdFeB permanent magnets

- Most important market, driving REE demand (NTE)
- High REE concentration (25% Nd, 5% Pr, 2-8% Dy)
- Immediate availability



Scheme for REE recovery and purification





Nuclear Energy Division - Marcoule RadioChemistry & Processes Department

Rare Earths 2016, Sapporo, Japan



RECAPE Process



Rare Earths 2016, Sapporo, Japan

June 9th 2016

DE LA RECHERCHE À L'INDUSTRIE

A well-tried approach to process development



Rare Earths 2016, Sapporo, Japan

Selection and evaluation of the extractant system



- Screening of several extracting molecules available at the laboratory
- Selection of diglycolamide (DGA) extractants for <u>selective Dy</u> <u>extraction versus Fe, B, Ni, Co and light REE</u>





- Selection of TODGA / TPH as solvent
- Addition of 5% octanol to prevent 3rd phase formation at high REE loading
- 0.2M TODGA + 5% octanol / TPH

RE Separation Process Development

- Tests on synthetic and genuine magnet solutions in nitric acid
- Quantitative extraction of Dy (D > 100)
- Efficient separation of RE / transition metals (Fe, Co, Ni...) and RE/RE in a large range of acidity (0.4 to 5 M)
- No 3rd phase formation in process conditions
- Quantitative stripping of Dy at low acidity (pH 3) and high temperature (45-50°C)





Confirmation of the potential of TODGA for selective Dy recovery from NdFeB magnet solutions



Process Modelling



Representation of distribution equilibria HNO₃-Oct, HNO₃-TODGA, Ln-NO₃-TODGA

- (HNO₃)(octanol)₂
- $(HNO_3)_m(TODGA)$ with m = 1 to 3

•
$$M(NO_3)_3(TODGA)_n$$
 with n = 3 for Dy, Nd, Pr, Fe

 $K'_{n} = \frac{\left[\{TR(NO_{3})_{3}, TODGA_{n}\}\right]}{\gamma_{TR(NO_{3})_{3}} \cdot [TR(NO_{3})_{3}] \cdot [\overline{TODGA}]^{n}}$



Good agreement between extraction experiments and calculated values for both synthetic and real solutions

Implementation of the model in the CEA PAREX simulation code and calculation of flow-sheets





Development of the separation process flowsheet

- Calculation of flow sheets in 1 or 2 cycles to recover Dy and Nd+Pr with theoretical purities > 99.5% in a limited number of stages
- Effective and compact process



Patent application 1459023: Procédés de récupération sélective de terres rares présentes dans des phases aqueuses acides issues du traitement d'aimants permanents usagés ou rebutés »



- Solution of NdFeB magnets in HNO₃ provided by CEA/DRT/LITEN
- Test in 16 stages of lab-scale mixer-settlers on PROUST platform (CEA / Marcoule)
- 1-cycle flowsheet for selective Dy recovery
- Nd & Pr collected in the raffinate for further 2nd cycle process









Pilot demonstration test on used magnets





Nuclear Energy Division - Marcoule RadioChemistry & Processes Department

Rare Earths 2016, Sapporo, Japan

June 9th 2016

Cez

Pilot demonstration test on used magnets

Test runned for 20 hours with solvent recycling (steady state reached)

Very good hydrodynamic behavior

UV-vis on-line analysis (for Nd) and ICP-AES measurements for Dy, Nd, Fe

- Quantitative recovery of Dy with very high purity
- Dy recovery > 99.7% with <u>purity > 99.99%</u>
 - Loss of only 1.7 mg/L of Dy in the raffinate
- Production of Dy concentrated from 0.69 to 4.05 g/L (×6)



Conversion of Dy to REO and metals in progress







Rare Earths 2016, Sapporo, Japan

DE LA RECHERCHE À L'INDUSTR

Pyrometallurgical process for metal elaboration

Objective: pyrometallurgical conversion of the separated REE into high purity RE metals.

Use of **transient electroanalytical techniques** (voltammetry reversal chronopotentiometry, chronoamperometry...)

to optimize the experimental condition:

- Salt composition
- Temperature
- Dy concentration
- Current and current density

Metal deposition tests to evaluate the process efficiency:

- Metal adherence
- Faradic yield
- Product purity
- Cell materials compatibility



y, Glovebox setup



Potential vs Ag/Ag+ reference electrode

on of 80%



Current (A)



Nuclear Energy Division - Marcoule RadioChemistry & Processes Department

Rare Earths 2016, Sapporo, Japan

June 9th 2016



Development of a full RE separation process from used permanent magnets

- Fruitful collaboration between CEA / DRT (magnet fabrication, front-end recycling process) and CEA / DEN (SX separation, RE conversion)
- Process patented for Dy and Nd recovery from permanent magnets
- Demonstration of the scientific feasibility of Dy recovery by SX without preliminary separation of Fe, B and the coating elements by precipitation
- Pilot scale production of highly pure Dy from real used magnets
 - Experiments in progress on Dy and Nd-Pr conversion to oxides (oxalic precipitation) and to metals (electrolysis in molten salts)
- Scale-up and technical-economic study of the process allowed the evaluation of the process cost at an industrial scale
 - Development of recycling processes for other WEEE or valuable materials
 - ANR « REPUTER » project on the recycling of REE from spent Ni-MH batteries



DE LA RECHERCHE À L'INDUSTRIE

cea

REPUTER - Recovery, purification and elaboration of rare earth elements for Ni-MH battery recycling





2 M€ budget REPUTER project started in 2016





Acknowledgments

<u>DEN/DRCP</u> V. Haquin (post doc) M-T Duchesne V. Pacary M. Miguirditchian M. Montuir J. Serp L. Diaz JC Thieblemont

> <u>DRT/Liten</u> R. Laucournet E. Bouyer

<u>DEN/Valo</u> B. Larousse

THANK YOU FOR ATTENTION

Commissariat à l'énergie atomique et aux énergies alternatives Centre de Marcoule | BP17171 | 30207 Bagnols-sur-Cèze Cedex eugen.andreiadis @ cea.fr Direction de l'énergie nucléaire Département de radiochimie des procédés Service de modélisation et de chimie des procédés de séparation