

Thermodynamic study of (U-Pu-Zr-O-Fe) corium system

A. Quaini, C. Gueneau, S. Gosse, T. Alpettaz, Emmanuelle Brackx, A.

Chocard, R. Domenger, D. Manara, K. Boboridis, P. Lajarge, et al.

▶ To cite this version:

A. Quaini, C. Gueneau, S. Gosse, T. Alpettaz, Emmanuelle Brackx, et al.. Thermodynamic study of (U-Pu-Zr-O-Fe) corium system. International Conference on Computer Coupling of Phase Diagrams and Thermochemistry - CALPHAD XLIV, May 2015, Loano, Italy. cea-02489508

HAL Id: cea-02489508 https://cea.hal.science/cea-02489508

Submitted on 24 Feb 2020

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers. L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés. DE LA RECHERCHE À L'INDUSTRIE




Andrea Quaini¹, <u>Christine Guéneau¹</u>, Stéphane Gossé¹, Thierry Alpettaz¹, Emmanuelle Brackx², Alexis Chocard², Renaud Domenger², Dario Manara³, Kostantinos Boboridis³, Patrick Lajarge³, Fiqiri Hodaj⁴

> ¹ DEN,DPC,SCCME,LM2T, CEA Saclay, 91191Gif-sur-Yvette Cedex, France, ² DEN,DTEC,SGCS,LMAC, CEA Marcoule, 30207 Bagnols sur Cèze Cedex, France ³ITU, JRC, EC, 76125 Karlsruhe, Germany ⁴ SIMAP, UMR CNRS 5266, 38402 Saint Martin d'Hères, France


CONTEXT AND PURPOSE OF THE WORK


In case of severe accident in a pressurized water reactor (PWR), the nuclear oxide fuel (UO_{2+x} or (U,Pu)O_{2+x}) could react with the Zr-alloy cladding and subsequently with the stainless steel vessel to form a mixture of solid and liquid phases, designated as "corium". The high temperature thermodynamic properties of this complex mixture have to be properly established to predict the corium behaviour during a severe accident. The approach is to develop a thermodynamic database using Calphad method on the (U-Pu-Zr-O-Fe) system that is representative for UO_{2+x} or $(U,Pu)O_{2+x}$ fuel, Zr-alloy cladding and steel vessel. A critical analysis of the available experimental data was first performed. Then an experimental work was carried out to provide new phase diagram data in U-Zr-O, Fe-Zr-O, UO₂-PuO₂-ZrO₂ sub-systems. Heat treatments in the U-Zr-O and Fe-Zr-O systems allowed for highlighting the existence of miscibility gaps in the liquid state in both systems. The advanced laser heating setup developed in ITU was used to measure temperatures of solid/liquid transitions in the UO₂-PuO₂-ZrO₂ sub-system. All the experimental data together with literature data were used to improve the thermodynamic modelling of the (U-Pu-Zr-O-Fe) system. Both experimental and calculated results will be presented on the different corium systems.




MISCIBILITY GAP IN THE U-ZR-O SYSTEM


- 4 samples (mixtures of U, Zr, ZrO₂) heated at 2567 K for 45 minutes in W crucibles
 2 metallic and oxide liquids
- Characterization using SEM, EDS, WDS \Rightarrow experimental tielines








Evolution of the sample overall composition due to « UO » vaporization



ATTILHA SETUP DEVELOPMENT

- Phase transition temperature measurements in Al_2O_3 -ZrO₂ system (10 mol. % ZrO₂)



CONCLUSION

- New experimental results on corium
- Tielines in liquid miscibility gap of U-Zr-O, U-Zr-O-Fe systems
- Phase transition temperature measurements in U-Zr-O, Fe-Zr-O and UO₂-PuO₂-ZrO₂ systems (ITU)
- Development of the ATTILHA new laser heating setup

Microstructure of the quenched sample

Improvement of the thermodynamic modelling

- UO₂-PuO₂-ZrO₂ system -
- U-Pu-Zr-Fe-O system

Application calculations for severe accidents

- Solidification paths to interpret the quenched microstructure
- Corium/concrete TAF-ID interaction (using database for concrete systems)

Calphad 2015, 31 May-5 June, Loano, Italy