

DE LA RECHERCHE À L'INDUSTRIE



LIBS APPLICATION IN JOINT EUROPEAN TORUS

**A. Semerok¹, D. L'Hermite², J.-M. Weulersse¹, J.-L. Lacour²,
C. Grisolia³, M. Kempenaars⁴, N. Bekris⁵**

¹CEA Saclay, DEN/DPC/SEARS/LISL, P.C. 56, 91191, Gif sur Yvette, France

²CEA Saclay, DEN/DPC/SEARS/LANIE, P.C. 56, 91191, Gif sur Yvette, France

³CEA Cadarache, IRFM/dir, 13108, St Paul lez Durance, France

⁴ EURATOM /CCFE Fusion Association, Culham Science Centre, Abingdon,
OX14 3DB, UK


⁵ JET-EFDA, Culham Science Centre, Abingdon OX14 3DB, UK

Problem: Tritium retention on the walls


ITER < 700 g

Laser methods to solve the problem:

- **LIBS for deposited layer in-depth characterisation**
(depth & composition)
- **Detritiation by:**
 - laser heating
 - laser ablation



Tritium trapping on the PFC




Deposited layer formation

- 10 nm (Be wall) – 100 µm (divertor)
- up to 50% of D/T
- solid - friable (porous)



JET (Joint European Torus), Culham, UK

JET – the biggest European thermonuclear installation.


Type	Tokamak
Major radius	2.96 m
Minor radius	1.25–2.10 m
Plasma volume	100 m ³
Magnetic field	3.45 T (toroidal)
Vacuum	10 ⁻⁸ Bar
Plasma	D/T
Operation date	1984–
Diagnostics: EDGE LIDAR	Thomson scattering



General layout of EDGE LIDAR Thomson scattering system




LIBS in situ application on JET



Ruby laser: 690 nm, 3 J; 300 ps,
 $\varnothing \geq 4$ mm, 80 GW/cm²,
one shot / 5 min.



LIBS system: plasma plume $\varnothing \approx 20$ mm;
NA of the collection system $\approx 1/40$; M $\approx 1/12$;
ANDOR Shamrok SR-303i spectrometer,
f=300mm, 1200mm⁻¹, NA = f/4; slit 200 μm .
ICCD camera



Target: W-stripe with D/Be
and impurities deposit
($\sim 10\text{-}100 \mu\text{m}$ thickness)

Experimental conditions for LIBS application in JET

- vacuum (10^{-8} Bar)
- distance - 5 m, with transportation - 7 m
- limited NA for light collection(125 mm on 5 m)
- target (vacuum chamber, non accessible)
- H/D/T (12 eV, thermal diffusion)
- Ruby laser (one shot / 5 min)
- limited experimental time (one week)



Experimental conditions for LIBS application in JET

$$\text{LIBS Signal(detected photons)} \cong N_a \times \frac{g_i e^{-Ei/kT}}{u(T)} \times A_{ij} \times$$




LIBS spectra with analytical Deuterium lines.

W-stripe zone with the deposited layer, vacuum, laser pulse energy ≈ 3.0 J, spectrometer slit width = 200 μm , grating -1800 mm^{-1} , ICCD camera delay = 180 ns, gate width = 2 μs .




Cr, C⁺, D γ , Be⁺, D α spectral lines are observed

Lifetime of analytical spectral lines D_α




LIBS spectra after the 1st and 11th laser shots on W-stripe zone with the deposited layer




LIBS spectrum after the first (shot nb 46) and 10th laser shot (shot nb 56) on the W-stripe zone with the deposited layer. Laser pulse energy – ≈ 3.0 J, spectrometer slit width = 200 μm , 1200 mm^{-1} , ICCD camera delay = 180 ns, gate width = 2 μs , vacuum.

Shot to shot spectral lines intensity evolution (layer on W-stripe)



The tiles observed after our experiments



CONCLUSIONS

Successful qualitative in situ LIBS application in JET (vacuum 10⁻⁸ Bar, ≈10 m, D_α / D_β / D_γ / Be⁺ / C⁺ / Cr);

Adequate understanding of the processes, problems and difficulties;

Possible improvements (fs/ps laser, collinear double pulse);

H/D/T isotope measurements (spectral resolution ≥ 10000);

Further steps – quantitative LIBS with ITER-like samples, Tokamak integration, and in situ validation.