

FUELBASE, TAF-ID DATABASES AND OC SOFTWARE: ADVANCED COMPUTATIONAL TOOLS TO PERFORM THERMODYNAMIC CALCULATIONS ON NUCLEAR FUEL MATERIALS

C. Guéneau¹, S. Gossé¹, A. Quaini¹, N. Dupin², B. Sundman³, M. Kurata⁴, T. Besmann⁵,
 P. Turchi⁶, J.-C. Dumas⁷, E. Corcoran⁸, M. Piro⁹, T. Ogata¹⁰, R. Hania¹¹, B.O. Lee¹²,
 R. Kennedy¹³, S. Massara¹⁴



¹ CEA, DEN, DPC, SCCME , 91191 Gif-sur-Yvette Cedex, France

² Calcul Thermodynamique, 63670 Orcet, France

³ CEA, INSTN, 91191 Gif-sur-Yvette Cedex, France

⁴ JAEA, Tokai-mura, Ibaraki-ken, 319-1195 Japan

⁵ ORNL, Oak Ridge, TN 37831, USA

⁶ LLNL, Livermore, USA



⁷ CEA, DEN, DEC, SESC, 13108 Saint-Paul lez Durance, France

⁸ RMC , Station Forces Kingston, Canada

⁹CNL, Chalk River, Ontario K0J 1J0, Canada

¹⁰ CRIEPI, Tokyo 201-8511, Japan

¹¹ NRG, NL-1755 LE Petten, Netherlands

¹² KAERI, Taejon 305600, South Korea

¹³ INL, Idaho Falls, ID 83415, USA



¹⁴ OECD, NEA, Nuclear Science Section, 92130 Issy-les-Moulineaux, France



Nuclear Energy




CONTEXT AND AIM OF THE TAF-ID PROJECT

AIM

- To develop a **thermodynamic database** as a **computational tool** to perform thermodynamic calculations on advanced fuel materials using the Calphad method
 - ➡ **Phase diagrams + Thermodynamic properties of the phases**
 - To facilitate the **exchange** on the models, review of experimental data, softwares, assessments
-


CONTEXT ➡ Fuel materials for Generation 2,3 & 4 reactors

- **Fuels**
 - UO_2 , $(\text{U},\text{Pu},\text{Am},\text{Np})\text{O}_2$, $(\text{U},\text{Th})\text{O}_2$, $(\text{U},\text{Pu},\text{Zr},\text{Am},\text{Np})$, UN , $(\text{U},\text{Pu})\text{C}$
- **Fission products**
 - Ba, Sr, Mo, Zr, Lanthanides (Ce, La, Nd, Gd), metallic FPs (Pd, Ru, Rh, Te), Volatile (Cs, I, Te)
- **Structural materials**
 - Fe-Cr-Ni, Zr alloys, Fe-Cr-Al-Y, Concrete (SiO_2 -CaO- Fe_xO_y - Al_2O_3 -MgO), SiC, B_4C




APPLICATIONS

- **Fuel behaviour at high temperature under normal and off-normal conditions**
 - Influence of the **Minor Actinides** on the fuel thermodynamic properties
 - **Fission product** « chemistry »
 - Solid/liquid phase transition
 - Vaporization
- **Fuel / cladding chemical interaction at high temperature**
- **Fuel fabrication**



CALPHAD METHOD

The thermodynamic equilibrium is calculated by minimizing the Gibbs energy of the system




$$G = \sum_{\alpha} m^{\alpha} \cdot G_m^{\alpha}$$

$$x_i = \sum_{\alpha} m^{\alpha} \cdot x_i^{\alpha}$$

$\min(G) = \min \left(\sum_{\alpha} m^{\alpha} G_m^{\alpha}(T, p, x_i^{\alpha} \text{ or } y_k^{(l, \alpha)}) \right)$

CALPHAD METHOD



FUELBASE DATABASE FOR ADVANCED NUCLEAR FUEL MATERIALS (2005-2012)

FUELBASE was a collaboration between CEA, Calcul Thermo, ITU, NRG and ORNL and served as the model for the expanded TAF-ID project

Am	C	Cr	Mo	N	Nb	Np	O	Pu	Re	Ru	Si	Ta	Ti	U	V	W	Zr
Am						Kurata 10	Gotcu 10	Dupin 07						Kurata 10			
	C	Andersson 87	Andersson 88	SGTE	Lee 01		SGTE	CEA 10	Dupin 07		Grobner 96	Frisk 96	Dumitrescu 98	Dupin 09	Huang 91	Jonsson 93	Guillemet 95
	Cr		Frisk 88	Frisk 91			Taylor 90	Dupin 06			Coughanowr 94		Saunders 98	Dupin 05	Lee 92		Zeng 98
	Mo		Frisk 91			Sundman 07	Dupin 05	Dupin 08		Liu 05		Chung 99	Dupin 06				Jerlerud 03
		N				SGTE	Sundman 05			Hillert 92		Jonsson 96	Chevalier 00	Ohtani 91			Ma 04
		Nb				Berche 09				Shao 04			Liu 08				Guillemet 91
		Np		Benes 09	Dupin 08								Kurata 10				
		O		Gueneau 08				Halsted 93			Sundman 05	Gueneau					Liang 01
		Pu		Berche 08	Dupin 08	Dupin 05	Berche 09	Dupin 06	Kurata 99	Berche 09	Berche 08	Berche 08	Berche 08				Kurata 99
		Re				Dupin				Berche 08			Dupin				
		Ru								Dupin 08							
						Si	Vahmas 89	Seifert 00	Berche 09				Vahmas 89	Gueneau 94			
						Ta			Berche 09								
						Ti	Rado 06	Saunders 98								Kumar 94	
						U	Berche 09	Sundman 07					Berche 09	Sundman 07	Chevalier 04		



JRC - Institute for Transuranium Elements



TAF-ID PROJECT

2013-2016: Thermodynamics of Advanced Fuels – International Database

► The aim is to make available a comprehensive, internationally recognised and quality-assured thermodynamic database for advanced fuels

Programme Review Group			
Country	Signatory	Representative	Alternate Member
Canada	CNL, RMCC, UOIT	M. Piro	E.C. Corcoran
France	CEA	C. Guéneau (Chair)	J.-C. Dumas
Japan	JAEA, CRIEPI	M. Kurata	T. Ogata
The Netherlands	NRG	R. Hania	G.-J. de Haas
Rep. Of Korea	KAERI	B.-O. Lee	J.-H. Kim
USA	DOE	T. Besmann (Vice-Ch)	P. Turchi

- The TAF-ID database is being built by merging existing databases
- N. Dupin (consultant) is responsible for maintenance and documentation
- Coordinated by S. Massara from OECD/NEA ➔ <http://www.oecd-nea.org/science/taf-id>

DATABASES DEVELOPED BY THE PARTNERS

Country	Software	Chemical system	Model
Canada AECL RMC UOIT	FACTSAGE	Fuel $\text{UO}_2 + \text{Np}$, $\text{Pu} + \text{Coolant H}_2\text{O}$ FPs: (Kr), Rb, Sr, Y, Zr, Mo, Tc, Ru, Rh, Pd Te, I, Xe, Cs, Ba, La, Ce, Pr, Nd	302 comp. 17 solutions
France CEA	Thermo-Calc	Fuel UO_2 , MOX+Am,Np,(U,Pu,Zr), (U,Pu)C, (U,Pu)N FPs: Ag, Ba, Cs, I, La, Mo, Nb, Ru, Sr, Te Materials: Concrete, B-C, Fe-Cr-Ni, SiC,Ta, W, V	Solutions 561 binaries 30 ternaries
Japan JAEA, CRIEPI	Thermo-Calc	Metallic fuel: Am-Cd-Ce-Fe-Gd-La-Nd-Np-Pr-Pu-U-Y-Zr Oxide fuel: Pu-Zr-O, Fe-B-C-O	Solutions
Netherlands NRG	FACTSAGE	Fuel: (U, Pu, Am, Np, Th)-(C, N, O) FPs: Ag, Ba, Br, Ce, Cs, Eu, I, La, Mo, Nb, Nd, Pd, Rb, Ru, Sb, Sn, Sr, Te, Y, Zr Materials: Fe, Ni, Si, Ti, Ta, W, Zn + Na, H, Pb	727 comp.
USA ORNL LLNL	FACTSAGE Thermo-Calc	$\text{UO}_2 + \text{RE}$: Pu-U-Gd-Ce-La-O Metallic fuel: Am-Pu, Mo-Pu,Mo-U,Nb-U,Nb-Zr,Pu-U,Ti-U,U-Zr Materials: Be-Cu-Fe-Nb-Ta-Ti-Zr	C1 solution solutions

- ▶ Different databases with different models.
- ▶ FACTSAGE and Thermo-Calc softwares are used.

THERMOCHEMICAL MODELS

Thermochemical models may be inconsistent between contributors and need to be reconciled

Models with stoichiometric phases and a few solid solutions

- TBASE+RMC+UOIT:** many compounds are described
- Associate model for oxide solid solutions ($A, AO_2, AO_3 \dots$)
 - The phase diagrams can not be calculated
 - A solution model for (Mo,Pd,Rh,Ru,Tc)

Models for MOX solid solution with Lanthanides

- ORNL:** determines oxygen potential versus burnup
- Ionic three sublattice model for MOX: Compatible with CEA database
 - Phase diagrams can be calculated

Models with a full description of non stoichiometric phases (solid & liquid)

- JAEA+CEA+LLNL** → The phase diagrams can be calculated

The aims of our project are:

- **Merge the different databases,**
- **Agree on thermodynamic descriptions** for binary and ternary sub-systems
- **Propose experiments** to improve the descriptions

TAF-ID DATABASE (VERSION 5 – JANUARY 2015)

ELEMENTS ➔ Ag-Al-Am-Ar-B-Ba-C-Ca-Ce-Cr-Cs-Fe-Gd-H-He-I-La-Mg-Mo-N-Nb-Nd-Ni-Np-O-Pd-Pu-Re-Rh-Ru-Si-Sr-Ta-Te-Th-Ti-U-V-W-Zr

Ag-I Ag-O Ag-Ti Ag-Zr
 Al-Ca Al-Cr Al-Fe Al-Mg Al-O Al-Si Al-U Al-Zr
 Am-Fe Am-Np Am-O* Am-Pu* Am-U Am-Zr
 B-C B-Fe B-H B-I B-O B-Pu B-U B-Zr
 Ba-H Ba-I* Ba-La* Ba-Mo* Ba-N Ba-O Ba-Ti* Ba-V*
 C-Cr C-Fe C-Mo C-N C-Nb C-Ni C-O C-Pu* C-Re C-Si C-Ta C-Ti C-U* C-V C-W C-Zr
 Ca-Fe Ca-Mg Ca-O Ca-Si Ca-U* Ca-Zr*
 Ce-Cr Ce-Fe Ce-O*
 Cr-Cs* Cr-Fe Cr-H Cr-I Cr-La* Cr-Mo Cr-N Cr-Nd* Cr-Ni Cr-O Cr-Pu* Cr-Si Cr-Ti Cr-U* Cr-Zr
 Cs-I* Cs-Mo* Cs-Nb* Cs-O Cs-Pu* Cs-Ta* Cs-Te* Cs-Ti* Cs-U* Cs-V* Cs-Zr*
 Fe-Nd Fe-Ni Fe-Np Fe-O Fe-Pu Fe-Si Fe-U Fe-Zr
 Gd-O Gd-U*
 H-I H-O H-Sr
 I-Mo I-Sr I-Te
 La-Mo* La-Nb* La-O La-Pu* La-Re* La-Ta* La-Te La-Ti* La-U* La-V* La-W*
 Mg-O Mg-U* Mg-Zr*
 Mo-N Mo-O Mo-Pd Mo-Pu* Mo-Re Mo-Rh* Mo-Ru Mo-Si Mo-Sr* Mo-Te* Mo-Ti Mo-U* Mo-Zr
 N-O N-Pu* N-Si N-Ti N-U N-Zr
 Nb-O Nb-Pu* Nb-Si Nb-U Nb-Zr
 Nd-O* Nd-U*
 Ni-O Ni-U
 Np-O* Np-Pu* Np-U Np-Zr
 O-Pu* O-Ru O-Si O-Sr O-Te O-Th* O-Ti O-U O-Zr
 Pd-Rh Pd-Ru* Pd-Tc* Pd-Te* Pd-Zr
 Pu-Re* Pu-Ru* Pu-Si* Pu-Ti* Pu-U Pu-W* Pu-Zr
 Re-Si Re-U* Re-W
 Rh-Ru* Rh-Tc* Rh-Te*
 Ru-Te* Ru-U*
 Si-Ta Si-Ti Si-U* Si-W Si-Zr
 Sr-Ti* Sr-V*
 Ta-U*
 Ti-U* Ti-Zr
 U-W* U-Zr

BINARY SYSTEMS

TERNARY SYSTEMS

Al-Ca-O Al-Cr-O Al-Fe-O Al-Mg-O
 Al-O-Si Al-O-U Al-O-Zr
 Am-O-Pu
 B-C-Fe B-C-U B-C-Zr B-Fe-Zr B-Pu-U
 C-Mo-Re C-Mo-Si C-Mo-Ti C-Mo-U C-N-Ti C-N-U
 C-O-Pu C-O-U C-Pu-U C-Pu-W C-Re-U C-Re-W
 C-Si-Ti C-Si-U C-U-W C-U-Zr
 Ca-Fe-O Ca-Mg-O Ca-O-Si Ca-O-U Ca-O-Zr
 Cr-Fe-O Cr-Fe-Zr
 Cs-Mo-O Cs-O-U Cs-O-Zr
 Fe-O-Si Fe-O-U Fe-O-Zr Fe-U-Zr
 Gd-O-U
 La-O-U
 Mg-O-Si Mg-O-U Mg-O-Zr
 Mo-O-U Mo-Pd-Rh Mo-Pd-Ru Mo-Rh-Ru
 Nb-O-U
 Nd-O-U
 Ni-O-Si
 O-Pu-U O-Pu-Zr O-Si-U O-Si-Zr O-U-Zr
 Pd-Rh-Ru
 Pu-U-Zr


In red*: 72 assessed within our project
 In blue: 116 coming from the literature

CRYSTALLOGRAPHIC DATA

TAF-ID : Thermodynamics of Advanced Fuels - International Database

	Home	Introduction	Models	Phases	Systems	
Phases described by						
usual name: ϵ -Pu...						
database name: BCC_A2...						
prototype: W...						
StrukturBericht: A2...						
Table						
BETA_RHOMBO_B	B	<i>hR105</i>	(B)			
BETA_SIALON	β -Si ₃ N ₄	<i>hP14</i>	(Si ⁴⁺) ₃ (N ³⁻) ₃ (N ³⁻)			
BF_CASI	BCr	<i>oC8</i>	<i>Bf</i>	(Ca) (Si)		
BH_MC_SHP	WC	<i>hP2</i>	<i>B_h</i>	(Mo, Re, W) (C)		
MoC, WC						
C1_MO2	CaF ₂	<i>cF12</i>	C1	(Al ³⁺ , Am ³⁺ , Am ⁴⁺ , Ca ²⁺ , Np ³⁺ , Np ⁴⁺ , Pu ³⁺ , Pu ⁴⁺ , Th ⁴⁺ , U ³⁺ , U ⁴⁺ , U ⁵⁺ , Zr ²⁺ , Zr ⁴⁺) (O ²⁻ , \emptyset) ₂ (O ²⁻ , \emptyset)		
UO ₂ , PuO ₂ , ZrO ₂ , AmO ₂ , NpO ₂						
C2_MTE2	FeS ₂	<i>cP12</i>	C2	(Rh, Ru, \emptyset) (Te) ₂		
Pyrite						
C4_RUTILE	TiO ₂	<i>tP6</i>	C4	(Ru ⁴⁺ , Ti ⁴⁺) (O ²⁻) ₂		
C4_TI2N	TiO ₂	<i>tP6</i>	C4	(Ti) ₂ (C, N)		
Described independently of TiO ₂						
C6_B81	NiAs	<i>hP4</i>	<i>B₈1</i>	(Pd, Rh) (Pd, Rh, \emptyset) (Te) ₂		
Identical model for CdI ₂						
C6_B81_2	CdI ₂	<i>hP3</i>	C6	(Pd, Rh, \emptyset)		
Identical model for NiAs						
C11B_AGM2	MoSi ₂	<i>tI6</i>	C11 _b	(Ag) (Si) ₂		
C11B_MOSI2	MoSi ₂	<i>tI6</i>	C11 _b	(Mo, Re) (Si) ₂		
C12_CASI2	CaSi ₂	<i>hR18</i>	C12	(Ca) (Si) ₂		
C14_LAVES	MgZn ₂	<i>hP12</i>	C14	(Cr, Fe) (Zn) ₂		
C15_LAVES	MgCu ₂	<i>cF8</i>	C15	(Al, Cr) (Cu) ₂		
C16_THETA	CuAl ₂	<i>tI12</i>	C16	(Ta, Zr) (Al) ₂		
C23_CA2SI	Co ₂ Si	<i>oP12</i>	C23	(Ca) ₂ Si		

TAF-ID : Thermodynamics of Advanced Fuels - International Database

Home	Introduction	Models	Phases	Systems												
Usual name ZrO ₂ -γ, PuO ₂ , UO ₂ , AmO ₂ , NpO ₂ , ThO ₂ Name in the database C1_MO2																
Crystallography Prototype CaF ₂ StrukturBericht C1 Pearson cF12 Space Group Fm-3m 																
Characteristics of the different sites for the prototype <table border="1" style="margin-left: auto; margin-right: auto;"> <tr> <th>Occupation</th> <th>Multiplicity</th> <th>Wickoff</th> <th>Symmetry</th> </tr> <tr> <td>F</td> <td>8</td> <td>c</td> <td>-43m</td> </tr> <tr> <td>Ca</td> <td>4</td> <td>a</td> <td>m-3m</td> </tr> </table>					Occupation	Multiplicity	Wickoff	Symmetry	F	8	c	-43m	Ca	4	a	m-3m
Occupation	Multiplicity	Wickoff	Symmetry													
F	8	c	-43m													
Ca	4	a	m-3m													
Thermodynamic model (Al ³⁺ , Am ³⁺ , Am ⁴⁺ , Ca ²⁺ , Np ³⁺ , Np ⁴⁺ , Pu ³⁺ , Pu ⁴⁺ , Th ⁴⁺ , U ³⁺ , U ⁴⁺ , U ⁵⁺ , Zr ²⁺ , Zr ⁴⁺) (O ²⁻ , \emptyset) ₂ (O ²⁻ , \emptyset)																
Assessed systems where the phase is stable Am-O Ce-O Np-O O-Pu O-Th O-U O-Zr Am-O-Pu C-O-Pu C-O-U Nd-O-U O-Pu-U O-Pu-Zr																

A single sublattice model for all the phases with the same crystalline structure

The source of the description is clearly mentioned.

TAF-ID : Thermodynamics of Advanced Fuels - International Database

Home

Introduction


Models

Phases

Systems

TDB

Binary system Al-Zr

[Al-O-Zr](#) [Al](#) [Zr](#) [Binary systems](#) [Ternary systems](#) [Periodic table](#)


Source of the description

T. Wang, Z. Jin, J.-C. Zhao, *J. phase equilibria*, **22** (5), 544-551, 2001.

Comments

The Al_2Zr and AlZr_3 descriptions are slightly modified in order to model them as the phases having the same prototype. The L1_2 phase corresponding to the AlZr_3 phase is rejected by default but restored by default when using the BINARY module of ThermoCalc.

File to calculate the phase diagram

[Al-Zr.TCM](#)

Cr-Fe-Zr

The source of the description is clearly mentioned.


TAF-ID : Thermodynamics of Advanced Fuels - International Database

[Home](#)
[Introduction](#)
[Models](#)
[Phases](#)
[Systems](#)
[TDB](#)


Ternary system Cr-Fe-Zr

[Cr-Fe](#) [Cr-Zr](#) [Fe-Zr](#) [Cr](#) [Fe](#) [Zr](#) [Binary systems](#) [Ternary systems](#) [Periodic table](#)

Isothermal section at 1500 K



Projection of the monovariant lines of the liquidus



Source of the description

N. Dupin, TAF-ID, 2014 october

Comments

The description recently published by Yang *et al.* was not used because of different descriptions for the Fe-Zr and Cr-Zr subsystems. The early description by Barberis *et al.* was using a Cr-Zr description with an overestimated enthalpy of formation for the Laves phases.

TAF-ID : Thermodynamics of Advanced Fuels - International Database

[Home](#)[Introduction](#)[Models](#)[Phases](#)[Systems](#)[TDB](#)


Ternary system Cr-Fe-Zr

[Cr-Fe](#) [Cr-Zr](#) [Fe-Zr](#) [Cr](#) [Fe](#) [Zr](#) [Binary systems](#) [Ternary systems](#) [Periodic table](#)


Comparison with experiments

Phase diagram

$T = 1148 \text{ K}$



$T = 1073 \text{ K}$






O-PU-U

TAF-ID : Thermodynamics of Advanced Fuels - International Database

[Home](#)
[Introduction](#)
[Models](#)
[Phases](#)
[Systems](#)

Ternary system O-Pu-U

[O-Pu](#) [O-U](#) [Pu-U](#) [O](#) [Pu](#) [U](#) [Binary systems](#) [Ternary systems](#) [Periodic table](#)



MOX fuel in SFR

- Interaction with steel clad
- Fission product chemistry

Source of the description

C. Guéneau, N. Dupin, B. Sundman, C. Martial, J.C. Dumas, S. Gossé, S. Chatain, F. De Bruycker, D. Manara, R. Konings, Thermodynamic modelling of advanced oxide and carbide nuclear fuels: Description of U-Pu-O-C systems, *J. Nuclear Materials*, **419** (2011) 145-167

O-U-Zr



TAF-ID : Thermodynamics of Advanced Fuels - International Database


[Home](#) [Introduction](#) [Models](#) [Phases](#) [Systems](#)

Ternary system O-U-Zr


O-U O-Zr U-Zr O U Zr Binary systems Ternary system

Comparison with experiments

Isothermal section at 2273K





Isothermal section at 2573K



Corium (U,Zr,O)
forming from
 UO_2/Zr interaction

UO₂-CONCRETE AND ZRO₂-CONCRETE INTERACTION



Corium (U,Zr,O,Fe)
forming from UO₂/Zr/Fe
interaction

UO₂ + ZrO₂
+ concrete

PUBLIC VERSION

[Home](#)[About Us](#)[Work Areas](#)[Data Bank](#)[Publications](#)[Delegates' Area](#)[Press Room](#)

Search


Nuclear science > Projects > TAF-ID

TAF-ID

[Thermodynamic data](#)
[Tools for thermodynamic calculations](#)
[Project Organisation](#)
[The TAF-ID Versions](#)
[Project Signatories](#)
[Relevant links](#)
[Contact](#)

Thermodynamics of Advanced Fuels – International Database (TAF-ID) Project

TAF-ID public version

The TAF-ID public version contains only data already published in the literature. Currently, the following systems are available in the public version:

- Oxide-Carbide fuel (U-Pu-O-C, released December 2014);
- Metal fuel (U-Pu-Zr, released December 2014).

This version is accessible free of charge to all NEA member countries upon request to the NEA and signature of a [Non-Disclosure Agreement \(NDA\)](#).

- To send to the NEA a signed copy of the Non-Disclosure Agreement (NDA) please [click here](#);
- If you already submitted a signed copy of the NDA and you received a confirmation e-mail, please directly enter the [restricted access zone](#) (password protected | reminder) and proceed to downloading.

Contact

For more information on the TAF-ID public version, please contact: taf-id@oecd-nea.org

For more information on TAF-ID, please contact: simone.massara@oecd.org

Last reviewed: 8 January 2015

TAF-ID working areas

[Programme review group](#)
[TAF-ID working version](#)
[TAF-ID public version](#)

OC: OPEN CALPHAD SOFTWARE (BO SUNDMAN)

- OC is an **open source** software to perform thermodynamic calculations using the CALPHAD method.
- OC uses as input data Databases containing mathematical models of the Gibbs energy as function of temperature, composition and pressure. **OC is compatible with databases in Thermo-Calc format (TDB).**
- A **grid minimizer** is used to provide an initial global minima as a start point for the equilibrium calculation. This solves the problems related to miscibility gaps.
- A **software interface module** is available to compute a thermodynamic equilibrium for given conditions (P, T, N, x_i) to provide input data to other softwares (diffusion, phase field, thermohydraulics, thermal ...).
- Calculations as function of temperature (or composition) can be performed.
- Binary phase diagrams can be calculated.
- A project is in progress to develop a **new assessment module** to develop the Gibbs Energy database.

RESULTS USING OC/TAF-ID ➔ IN-VESSEL CORIUM

In-vessel EPR corium: n(fe)=0.413601 n(o)=0.48623376 n(u)=0.19442428 n(zr)=0.250339

Output for equilibrium: 1, DEFAULT_EQUILIBRIUM

Conditions

1:T=2900, 2:P=100000, 3:N(FE)=0.413601, 4:N(O)=0.48623376, 5:N(U)=0.19442428, 6:N(ZR)=0.250339

Degrees of freedom are 0

Some global data, reference state SER

T= 2900.00 K (2626.85 C), P= 1.0000E+05 Pa, V= 0.0000E+00 m3

N= 1.3446E+00 moles, B= 9.9993E+01 g, RT= 2.4112E+04 J/mol

G= -5.6581E+05 J, G/N= -4.2080E+05 J/mol, H= -1.2890E+05 J, S= 1.5066E+02 J/K

Some component data

Component name	Moles	Mole-fr	Chem.pot/RT	Activities	Ref.state
FE	4.1360E-01	0.30760	-9.8791E+00	5.1234E-05	SER (default)
O	4.8623E-01	0.36162	-2.6262E+01	3.9298E-12	SER (default)
U	1.9442E-01	0.14460	-1.6957E+01	4.3218E-08	SER (default)
ZR	2.5034E-01	0.18618	-1.3235E+01	1.7863E-06	SER (default)

Some Phase data

Phase: LIQUID Status: Entered Driving force: 0.0000E+00

Moles 5.8403E-01, Mass 5.1195E-02 kg, Volume 0.0000E+00 m3

Formula Units: 2.2580E-01, Moles of atoms/FU: 2.5865E+00, Molar content:

FE 7.08188E-01 U 1.48903E-01 ZR 1.37959E-01 O 4.94951E-03

Constitution:

Sublattice 1 with 3 constituents and 2.573713 sites

FE+2 7.11711E-01 U+4 1.49644E-01 ZR+4 1.38645E-01

Sublattice 2 with 4 constituents and 2.576578 sites

VA 9.95031E-01 O 1.77141E-07

O-2 4.96842E-03 FEO3/2 1.00000E-12

Phase: C1_MO2 Status: Entered Driving force: 0.0000E+00

Moles 7.6057E-01, Mass 4.8799E-02 kg, Volume 0.0000E+00 m3

Formula Units: 2.7723E-01, Moles of atoms/FU: 2.7435E+00, Molar content:

O 6.35500E-01 ZR 2.23210E-01 U 1.41290E-01 FE 0.00000E+00

Constitution:

Sublattice 1 with 5 constituents and 1.000000 sites

U+4 3.72682E-01 ZR+2 2.49045E-01 U+3 1.49417E-02 U+5 2.51318E-06 ZR+4 3.63329E-01

Sublattice 2 with 2 constituents and 2.000000 sites

O-2 8.71743E-01 VA 1.28257E-01

Sublattice 3 with 2 constituents and 1.000000 sites

VA 1.00000E+00 O-2 4.50893E-08

RESULTS USING OC/TAF-ID ➔ IN-VESSEL CORIUM

In-vessel EPR corium: n(fe)=0.413601 n(o)=0.48623376 n(u)=0.19442428 n(zr)=0.250339

Output for equilibrium: 1, DEFAULT_EQUILIBRIUM

Conditions

1:T=3000, 2:P=100000, 3:N(FE)=0.413601, 4:N(O)=0.48623376, 5:N(U)=0.19442428, 6:N(ZR)=0.250339

Degrees of freedom are 0

Some global data, reference state SER

T= 3000.00 K (2726.85 C), P= 1.0000E+05 Pa, V= 0.0000E+00 m³

N= 1.3446E+00 moles, B= 9.9993E+01 g, RT= 2.4944E+04 J/mol

G= -5.8167E+05 J, G/N= -4.3260E+05 J/mol, H= -9.5706E+04 J, S= 1.6199E+02 J/K

Some component data

Component name	Moles	Mole-fr	Chem.pot/RT	Activities	Ref.state
FE	4.1360E-01	0.30760	-9.9398E+00	4.8219E-05	SER (default)
O	4.8623E-01	0.36162	-2.5505E+01	8.3826E-12	SER (default)
U	1.9442E-01	0.14460	-1.7408E+01	2.7536E-08	SER (default)
ZR	2.5034E-01	0.18618	-1.3671E+01	1.1550E-06	SER (default)

Component name	Moles	Mole-fr	Chem.pot/RT	Activities	Ref.state
FE	4.1360E-01	0.30760	-9.9398E+00	4.8219E-05	SER (default)
O	4.8623E-01	0.36162	-2.5505E+01	8.3826E-12	SER (default)
U	1.9442E-01	0.14460	-1.7408E+01	2.7536E-08	SER (default)
ZR	2.5034E-01	0.18618	-1.3671E+01	1.1550E-06	SER (default)

Component name	Moles	Mole-fr	Chem.pot/RT	Activities	Ref.state
FE	4.1360E-01	0.30760	-9.9398E+00	4.8219E-05	SER (default)
O	4.8623E-01	0.36162	-2.5505E+01	8.3826E-12	SER (default)
U	1.9442E-01	0.14460	-1.7408E+01	2.7536E-08	SER (default)
ZR	2.5034E-01	0.18618	-1.3671E+01	1.1550E-06	SER (default)

Component name	Moles	Mole-fr	Chem.pot/RT	Activities	Ref.state
FE	4.1360E-01	0.30760	-9.9398E+00	4.8219E-05	SER (default)
O	4.8623E-01	0.36162	-2.5505E+01	8.3826E-12	SER (default)
U	1.9442E-01	0.14460	-1.7408E+01	2.7536E-08	SER (default)
ZR	2.5034E-01	0.18618	-1.3671E+01	1.1550E-06	SER (default)

Component name	Moles	Mole-fr	Chem.pot/RT	Activities	Ref.state
FE	4.1360E-01	0.30760	-9.9398E+00	4.8219E-05	SER (default)
O	4.8623E-01	0.36162	-2.5505E+01	8.3826E-12	SER (default)
U	1.9442E-01	0.14460	-1.7408E+01	2.7536E-08	SER (default)
ZR	2.5034E-01	0.18618	-1.3671E+01	1.1550E-06	SER (default)

Component name	Moles	Mole-fr	Chem.pot/RT	Activities	Ref.state
FE	4.1360E-01	0.30760	-9.9398E+00	4.8219E-05	SER (default)
O	4.8623E-01	0.36162	-2.5505E+01	8.3826E-12	SER (default)
U	1.9442E-01	0.14460	-1.7408E+01	2.7536E-08	SER (default)
ZR	2.5034E-01	0.18618	-1.3671E+01	1.1550E-06	SER (default)

Some Phase data

Phase: LIQUID Status: Entered Driving force: 0.0000E+00

Moles 8.1749E-01, Mass 5.7516E-02 kg, Volume 0.0000E+00 m³

Formula Units: 1.4424E-01, Moles of atoms/FU: 5.6677E+00, Molar content:

O 5.92126E-01 ZR 2.42115E-01 U 1.62142E-01 FE 3.61699E-03

Constitution:

Sublattice 1 with 3 constituents and 2.311727 sites

ZR+4 5.93602E-01 U+4 3.97530E-01 FE+2 8.86791E-03

Sublattice 2 with 4 constituents and 3.982264 sites

O-2 8.42740E-01 O 1.13229E-06

VA 1.57259E-01 FEO3/2 1.00000E-12

Phase: OXID_LIQUID#2 Status: Entered Driving force: 0.0000E+00

Moles 5.2710E-01, Mass 4.2477E-02 kg, Volume 0.0000E+00 m³

Formula Units: 2.1570E-01, Moles of atoms/FU: 2.4437E+00, Molar content:

FE 7.79057E-01 U 1.17385E-01 ZR 9.94327E-02 O 4.12613E-03

Constitution:

Sublattice 1 with 3 constituents and 2.433628 sites

FE+2 7.82284E-01 U+4 1.17871E-01 ZR+4 9.98447E-02

Sublattice 2 with 4 constituents and 2.435431 sites

VA 9.95860E-01 O 4.95523E-07

O-2 4.13966E-03 FEO3/2 1.00000E-12

RESULTS USING OC/TAF-ID → EX-VESSEL CORIUM

Ex-vessel corium: mass. % Al₂O₃ 1.8 CaO 32.4 SiO₂ 24.6 UO₂ 38.8 ZrO₂ 18.4

Output for equilibrium: 1, DEFAULT_EQUILIBRIUM

Conditions

1:N(AL)=.0353, 2:N(CA)=0.57776, 3:N(SI)=0.40943, 4:N(U)=0.114062, 5:N(ZR)=.0844, 6:N(O)=1.85, 7:T=1700, 8:P=100000

Degrees of freedom are 0

Some global data, reference state SER

T= 1700.00 K (1426.85 C), P= 1.0000E+05 Pa, V= 0.0000E+00 m3

N= 3.0710E+00 moles, B= 1.0006E+02 g, RT= 1.4135E+04 J/mol

G= -1.2386E+06 J, G/N= -4.0334E+05 J/mol, H= -8.9264E+05 J, S= 2.0353E+02 J/K

Some component data

Component name	Moles	Mole-fr	Chem.pot/RT	Activities	Ref.state
AL	3.5300E-02	0.01149	-3.9744E+01	5.4895E-18	SER (default)
CA	5.7776E-01	0.18814	-3.8105E+01	2.8250E-17	SER (default)
O	1.8500E+00	0.60242	-2.0816E+01	9.1189E-10	SER (default)
SI	4.0943E-01	0.13332	-3.7248E+01	6.6559E-17	SER (default)
U	1.1406E-01	0.03714	-5.3410E+01	6.3717E-24	SER (default)
ZR	8.4400E-02	0.02748	-5.1673E+01	3.6212E-23	SER (default)

Some Phase data

Phase: OXID_LIQUID#2 Status: Entered Driving force: 0.0000E+00

Moles 2.3195E+00, Mass 5.4779E-02 kg, Volume 0.0000E+00 m3

Formula Units: 2.1708E-01, Moles of atoms/FU: 1.0685E+01, Molar content:

O 5.89762E-01 SI 1.71915E-01 ZR 1.45910E-07 U 7.88385E-08

CA 2.23105E-01 AL 1.52180E-02

Phase: CAUO4_S2 Status: Entered Driving force: 0.0000E+00

Moles 7.6863E-03, Mass 4.3825E-04 kg, Volume 0.0000E+00 m3

Formula Units: 1.2810E-03, Moles of atoms/FU: 6.0000E+00, Molar content:

O 6.66667E-01 U 1.66667E-01 ZR 0.00000E+00 AL 0.00000E+00

CA 1.66667E-01 SI 0.00000E+00

Phase: RANKINITE Status: Entered Driving force: 0.0000E+00

Moles 6.4009E-02, Mass 1.5384E-03 kg, Volume 0.0000E+00 m3

Formula Units: 5.3341E-03, Moles of atoms/FU: 1.2000E+01, Molar content:

O 5.83333E-01 SI 1.66667E-01 ZR 0.00000E+00 AL 0.00000E+00

CA 2.50000E-01 U 0.00000E+00

Phase: C1_MO2 Status: Entered Driving force: 0.0000E+00

Moles 1.0150E-01, Mass 8.6351E-03 kg, Volume 0.0000E+00 m3

Formula Units: 3.3828E-02, Moles of atoms/FU: 3.0004E+00, Molar content:

O 6.66706E-01 CA 2.17836E-02 AL 9.10416E-07 SI 0.00000E+00

U 3.07356E-01 ZR 4.15360E-03

Phase: C1_MO2_ZRO2#2 Status: Entered Driving force: 0.0000E+00

Moles 5.7823E-01, Mass 3.4665E-02 kg, Volume 0.0000E+00 m3

Formula Units: 2.0633E-01, Moles of atoms/FU: 2.8024E+00, Molar content:


O 6.43166E-01 U 1.41095E-01 AL 2.42748E-06 SI 0.00000E+00

ZR 1.45233E-01 CA 7.05034E-02

RESULTS USING OC/TAF-ID

Ex-VESSEL corium:

$N(O)=1.85$, $N(U)=0.255$, $N(ZR)=0.196$, $N(FE)=0.141$, $N(CR)=.032$, $N(SI)=0.279$, $N(AL)=.05$, $N(CA)=.088$



SUMMARY

- **The Working Version 5 of TAF-ID database is available for the participants of the TAF-ID project**
- **A public version restricted to only published work is available for all the member countries of OECD/NEA since december 2014**
 - ➔ <https://www.oecd-nea.org/science/taf-id/taf-id-public/>
- **The TAF-ID database will be available in Thermo-Calc and FACTSAGE formats**
 - **A software to convert the databases from both codes is being developed**
- **The TAF-ID project may be extended for 3 years**
- **OC is an open source software for CALPHAD calculations, compatible with Thermo-Calc format (TDB)**
- **Both OC and TAF-ID are operational computational tools to perform thermodynamic calculations on corium systems for severe accident applications**