



HAL
open science

High temperature creep study of recrystallized Tungsten: 3-point bending experiments and finite element simulation

J.-B. Parise, P. Garcia, T. Helfer, A. Miard, A. Durif, M. Richou, G. Antou

► **To cite this version:**

J.-B. Parise, P. Garcia, T. Helfer, A. Miard, A. Durif, et al.. High temperature creep study of recrystallized Tungsten: 3-point bending experiments and finite element simulation. Plasma-Facing Materials and Components for Fusion Applications (PFMC) 2019, May 2019, Eindhoven, Netherlands. . cea-02972214

HAL Id: cea-02972214

<https://cea.hal.science/cea-02972214v1>

Submitted on 20 Oct 2020

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

High temperature creep study of recrystallized Tungsten: 3-point bending experiments and finite element simulation

JB. Parise^a, P. Garcia^a, T. Helfer^a, A. Miard^a, A. Durif^b, M. Richou^b, G. Antou^c

^aCEA, DEN, DEC

^bCEA - IRFM

^cUniv. Limoges, IRCER, UMR CNRS 7315

DE LA RECHERCHE À L'INDUSTRIE

cea

CADARACHE

irCer

institut de recherche sur les céramiques


IRFM

Introduction / Objectives

Tungsten is a candidate as plasma-facing material for fusion reactors. It will operate at high temperature, under irradiation and under high thermal stresses over long periods of time. These operating conditions will cause it to creep and possibly fail as a result^[1]. Understanding its mechanical behaviour under such conditions is therefore essential.


The ultimate aim of this study is to establish a constitutive law describing the creep behaviour of recrystallized Tungsten, based on a range of mechanical tests which include high temperature 3-point bending in association with FEM. We report here preliminary tests and results of simulations carried out using the Frederick-Armstrong law describing kinematic hardening.

Materials




Made by rolling
• Elongated textured grains

Tungsten bending samples



Dimension
L = 28 mm
b = 8 mm
e = 1 mm

Recrystallized Tungsten




Heat treatment
1700°C for 3h : batch A
1700°C for 2h : batch B
Under Argon + 5% Hydrogen

Equipment

Three-point bending machine equipped with furnace



- Tungsten furnace can heat up to 1800°C
- Upper column and central point displacement monitored with two LVDTs. Displacement measurements are within a micron.





Displacement measurements

Equipment usually used on ceramics.

Many pieces of the device are made of Tungsten which spend many hours at high temperature.

Finite Element Simulation

2D and 3D FEM model



Frederick-Armstrong law^[2] viscoplastic constitutive law with kinematic hardening describing primary creep

$$\dot{\epsilon}_p = \left(\frac{\sigma - X}{K} \right)^n$$

$$\dot{X} = \frac{2}{3} C \dot{\epsilon}_p - DX \dot{p}$$

licos@Cast3m^[3] code used for the numerical calculations

Mfront^[4] code used for the implementation of the constitutive law



Finite logarithmic strain approximation

Simulation of a three-point bending creep test, at 1500°C, with a constant crosshead speed of 100µm/min


Longitudinal symmetry: only half beam is modelled
Upper and lower supports: rigid body displacement

Experimental upper support displacement is applied onto the beam (point A): the constitutive law is optimised with the numerical load curve

Adequate representation of material behaviour



Von Mises stress distribution in deformed beam




* cf. prospects

Results

Constant crosshead speed test: from 20 µm/min ($\dot{\epsilon} = 3,2 \cdot 10^{-6} s^{-1}$) to 200 µm/min ($\dot{\epsilon} = 3,2 \cdot 10^{-5} s^{-1}$)


Conditions
1500°C & flowing mixture of Argon + 5% Hydrogen

Except one test accidentally carried out under a static atmosphere



High deflection rate
70 to 200 µm/min
Low deflection rate
20 to 30 µm/min



These tests point out:



- Hardening phenomenon (load increases with the deflection)
- Two domains : low deflection rate (20 to 30 µm/min) and high deflection rate (more than 70 µm/min)
- At high deflection rates at least, small crosshead speed influence upon material behaviour: similar flow stress for tests between 70 to 200 µm/min. However, the steady-state creep is consistent with the strain rate (i.e. σ increasing function of $\dot{\epsilon}$)
- Some inconsistencies during the primary creep: load applied is lower at 200µm/min than at 100µm/min
- Strong effect of environment

Reproducibility of our tests ? Plastic or viscoplastic behaviour ? Atmosphere effect ?

A. Reproducibility




Several three-point bending tests with identical strain rate:

- Left: two samples from two batches (A & B) at 20 µm/min
- Right: two samples from same batch (B) at 30 µm/min

Consistent behaviour of our material


B. Relaxation test



Load progressively decreases during relaxation stage

True viscoplastic behaviour

C. Atmosphere influence



Starting $pO_2 = 1 \cdot 10^{-12}$ atm Ending $pO_2 = 2 \cdot 10^{-11}$ atm

Two similar creep tests:

- Imposed deflection rate of 30 µm/min
- At 1500°C

But:

- Sudden increase of the oxygen partial pressure during the second test

No particular effect on the behaviour

Conclusions / Prospects

- We carried out multiple three-point bending creep test on recrystallized Tungsten bars at 1500°C.
- Tests are modelled using Frederick-Armstrong behaviour law
- Some questions remain before we can establish a proper constitutive law:

1. Two distinct group of tests were observed at low and high deflection rates.
2. Inconsistencies in primary creep of high deflection rates.

- We feel that these issues may only be resolved through characterisations of microstructure (raw, after recrystallization and after deformation).
- Dynamic recrystallization effects^[5] (*) might explain the behaviour at early stages of the material

References

- [1] Rieth et al., Tungsten as a Structural Divertor Material. Advances in Science and Technology, Vol. 73. 2010
- [2] J. Lemaître and J.L. Chaboche, Mécanique des matériaux solides, 1988. Ed. Dunod
- [3] Helfer et al. J. Nuc. Eng. & Des. 294 (2015) <http://www-cast3m.cea.fr>
- [4] Helfer et al. Computers & mathematics with applications 70 (2015)
- [5] Poliak and Jonas. Acta mater. 1996.