



**HAL**  
open science

# Confined water in aluminosilicate nanotubes: Structure, dynamics and importance of charge separation effects upon irradiation

Sophie Le Caër

## ► To cite this version:

Sophie Le Caër. Confined water in aluminosilicate nanotubes: Structure, dynamics and importance of charge separation effects upon irradiation. ACS Spring meeting 2021 - Macromolecular Chemistry: The Second Century, ACS, Apr 2020, Online, United States. cea-03289959

**HAL Id: cea-03289959**

**<https://cea.hal.science/cea-03289959>**

Submitted on 19 Jul 2021

**HAL** is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

## Confined water in aluminosilicate nanotubes: Structure, dynamics and importance of charge separation effects upon irradiation

Sophie Le Caër

*NIMBE, UMR 3685 CEA, CNRS, Université Paris-Saclay, CEA Saclay 91191 Gif-sur-Yvette Cedex, France; Email: [sophie.le-caer@cea.fr](mailto:sophie.le-caer@cea.fr)*

Imogolite nanotubes are potentially promising co-photocatalysts because they are predicted to have curvature-induced, efficient electron-hole pair separation. This prediction has however not yet been experimentally proven. Here, we investigated the behavior upon irradiation of these inorganic nanotubes as a function of their water content to understand the fate of the generated electrons and holes.<sup>1</sup> Two types of aluminosilicate nanotubes were studied: one is hydrophilic on its external and internal surfaces (IMO-OH) and the other has a hydrophobic internal cavity due to Si-CH<sub>3</sub> bonds (IMO-CH<sub>3</sub>), with the external surface remaining hydrophilic (AlOH groups). The pre-requisite to such a study is a detailed understanding of the structure and dynamics of water in these nanotubes. Analysis of the O-H stretching band as a function of the relative humidity (RH) provided information on the H bonding of confined water molecules.<sup>2</sup> Adsorption begins in the IMO-OH tubes at the lowest RH (< 10%). The inner surface of the tubes is first covered with water molecules; then, the central part of the tubes is filled, leading to very strong H-bonds. In contrast, the H bonds of water adsorbed on the outer surfaces of these tubes are weaker. Water dynamics in IMO-OH was also revealed by quasi-elastic neutron scattering experiments.<sup>3</sup> When one water monolayer is present on the inner surface, water molecules can jump between neighboring Si-OH sites. When IMO-OH is filled with water, the H-bond network is very rigid, and water molecules are immobile on the timescale of the experiment. A different scenario is observed for water inside IMO-CH<sub>3</sub>. Weakly H-bonded water molecules are present. Water confinement in imogolites is then governed by the hydrophilicity of the inner walls. Upon irradiation, picosecond pulse radiolysis experiments demonstrated that the electrons are efficiently driven outward.<sup>1</sup> For imogolite samples with very few external water molecules, quasi-free electrons are formed. They are able to attach to a water molecule, which ultimately leads to dihydrogen. When more external water molecules are present, solvated electrons, precursors of dihydrogen, are formed. In contrast, holes move towards the internal surface. The attachment of the quasi-free electron to water is a very efficient process and accounts for the high dihydrogen production at low RH values. Our experiments demonstrate the spontaneous curvature-induced charge separation in these inorganic nanotubes.

### References

<sup>1</sup> "Confined water radiolysis in aluminosilicate nanotubes: the importance of charge separation effects", M.-C. Pignié, V. Shcherbakov, T. Charpentier, M. Moskura, C. Carteret, S. Denisov, M. Mostafavi, A. Thill, S. Le Caër, *Nanoscale*, 13, 3092 (2021).

<sup>2</sup> "Tuning the properties of confined water in standard and hybrid nanotubes: An infrared spectroscopic study", Y. Liao, P. Picot, M. Lainé, J.-B. Brubach, P. Roy, A. Thill, S. Le Caër, *Nano Research*, 11, 4759 (2018).

<sup>3</sup> "Dynamics in hydrated inorganic nanotubes studied by neutron scattering: towards nanoreactors in water", S. Le Caër, M.-C. Pignié, Q. Berrod, V. Grzimek, M. Russina, C. Carteret, A. Thill, J.-M. Zanotti, J. Teixeira, *Nanoscale Adv.*, 3, 789 (2021).