



**HAL**  
open science

## Understanding self-discharge or what's going on inside a lead-acid battery when nothing happens outside

Mikael Cugnet, Florian Gallois, Angel Kirchev, Denys Dutykh

### ► To cite this version:

Mikael Cugnet, Florian Gallois, Angel Kirchev, Denys Dutykh. Understanding self-discharge or what's going on inside a lead-acid battery when nothing happens outside. AABC Europe - 12th International Advanced Automotive Battery Conference, Jun 2022, Mainz, Germany. cea-03715092

**HAL Id: cea-03715092**

**<https://cea.hal.science/cea-03715092>**

Submitted on 6 Jul 2022

**HAL** is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

# Understanding self-discharge

What's going on inside a lead-acid battery when nothing happens outside?

Mikaël Cugnet<sup>1,2</sup>, Florian Gallois<sup>1,2,3,4</sup>, Angel Kirchev<sup>1,2</sup>, and Denys Dutykh<sup>4</sup>

<sup>1</sup>Université Grenoble Alpes, INES, F-73375 Le Bourget-du-Lac, France

<sup>2</sup>CEA, LITEN, Solar Technology Dept, F-73375 Le Bourget-du-Lac, France

<sup>3</sup>Haulotte Group, F-42420 Lorette, France

<sup>4</sup>Laboratory of Mathematics, UMR 5127, F-73375 Le Bourget-du-Lac, France

12<sup>th</sup> International AABC Europe, 13 June 2022, Mainz, Germany



# Outline

## 1 Introduction

# Outline

- 1 Introduction
- 2 Self-discharge of lead-acid cells



# Outline

- 1 Introduction
- 2 Self-discharge of lead-acid cells
- 3 Modeling self-discharge of a lead-acid cell

# Outline

- 1 Introduction
- 2 Self-discharge of lead-acid cells
- 3 Modeling self-discharge of a lead-acid cell
- 4 Conclusion

# Outline

- 1 Introduction
  - What is self-discharge?
  - Why self-discharge?
- 2 Self-discharge of lead-acid cells
- 3 Modeling self-discharge of a lead-acid cell
- 4 Conclusion



# What is self-discharge?

- Self-discharge is a set of processes that decreases the performance of electrochemical power sources without flow of current through an external circuit.



# What is self-discharge?

- Self-discharge is a set of processes that decreases the performance of electrochemical power sources without flow of current through an external circuit.
- Batteries that are prone to self-discharge exhibit a short shelf life and are thus disfavored in most applications.



# What is self-discharge?

- Self-discharge is a set of processes that decreases the performance of electrochemical power sources without flow of current through an external circuit.
- Batteries that are prone to self-discharge exhibit a short shelf life and are thus disfavored in most applications.
- Self-discharge is more critical for primary batteries than secondary batteries:
  - Primary batteries  $\Rightarrow$  short life
  - Secondary batteries  $\Rightarrow$  low energy efficiency



# Why self-discharge is so important?

- It may have dramatic consequences for systems that cannot be powered.

# Why self-discharge is so important?

- It may have dramatic consequences for systems that cannot be powered.
- It requires excessive charging that may be detrimental to the batteries.

# Why self-discharge is so important?

- It may have dramatic consequences for systems that cannot be powered.
- It requires excessive charging that may be detrimental to the batteries.
- It demonstrates that batteries remain active even though they are unused:

$$\forall \delta t > 0, \quad \frac{di}{dt} \leq 0, \quad i = 0 \quad \Rightarrow \quad u(t + \delta t) < u(t)$$

# Why self-discharge is so important?

- It may have dramatic consequences for systems that cannot be powered.
- It requires excessive charging that may be detrimental to the batteries.
- It demonstrates that batteries remain active even though they are unused:

$$\forall \delta t > 0, \quad \frac{di}{dt} \leq 0, \quad i = 0 \quad \Rightarrow \quad u(t + \delta t) < u(t)$$

**This feature is neglected in most battery models for simplicity!**

# Outline

- 1 Introduction
- 2 Self-discharge of lead-acid cells
  - Specific self-discharge processes
  - Experimental work
  - Reference electrode
  - Working electrode
- 3 Modeling self-discharge of a lead-acid cell
- 4 Conclusion

# Electrochemical reactions at each electrode

Hydrolysis of water, corrosion of the grid, and recombination of water

## Positive electrode



Cathodic:  $\text{PbO}_2 + \text{H}_2\text{SO}_4 + 2\text{H}^+ + 2\text{e}^- \rightleftharpoons \text{PbSO}_4 + 2\text{H}_2\text{O}$  (discharge)

Anodic:  $\begin{cases} \text{H}_2\text{O} \rightleftharpoons \frac{1}{2}\text{O}_2 + 2\text{H}^+ + 2\text{e}^- & \text{(oxygen evolution)} \\ \text{Pb} + \text{H}_2\text{O} \rightleftharpoons \text{PbO} + 2\text{H}^+ + 2\text{e}^- & \text{(grid corrosion)} \end{cases}$



# Electrochemical reactions at each electrode

Hydrolysis of water, corrosion of the grid, and recombination of water

## Positive electrode



## Negative electrode




# Redox shuttle process


Insufficiently purified water or leaching impurities from cell components

Impurities, e.g.  $\text{Fe}^{2+}/\text{Fe}^{3+}$ , lead to discharging of the cell by means of a so-called redox shuttle process:

## Positive electrode



## Negative electrode




This process continues as long as the electrode potentials allow the oxidation and reduction of ions. The redox shuttle ions themselves are not consumed.

# Redox shuttle process


Insufficiently purified water or leaching impurities from cell components

Impurities, e.g.  $\text{Fe}^{2+}/\text{Fe}^{3+}$ , lead to discharging of the cell by means of a so-called redox shuttle process:

## Positive electrode



## Negative electrode



This process continues as long as the electrode potentials allow the oxidation and reduction of ions. The redox shuttle ions themselves are not consumed.





Fig. 3. Hydrogen evolution in sulfuric acid at various metal surfaces in a semilogarithmic plot vs. electrode potential (polarization). The origin of the horizontal scale is the equilibrium potential of the hydrogen electrode.

D. Berndt, J. Power Sources 95 (2001) 2-12

## Some other self-discharge processes

### Reactions between positive active material and separator

Lead dioxide has a very high oxidation potential and can discharge in contact with separators:




The degradation of the separator must be avoided by proper choice of materials and designs.

## Some other self-discharge processes

### Reactions between positive active material and separator

Lead dioxide has a very high oxidation potential and can discharge in contact with separators:




The degradation of the separator must be avoided by proper choice of materials and designs.

### Ohmic Leakage Currents / Short Circuits

- New lead–acid batteries do not exhibit such self-discharge phenomena.
- Short circuits (e.g., formation of dendrites through the separator) can develop after long use and soon lead to cell failure, as they enable a discharging process inside the cell.
- A conductive layer of dirt on the cell container may bridge the battery terminals, but discharging caused by such fault currents can be reversed by the charging process.

# Self-discharge in practice

Example of a flooded lead-acid battery for traction applications



# Self-discharge in practice

Tear-down of an individual electrochemical cell

- Number and dimensions of positive and negative electrodes

# Self-discharge in practice

Tear-down of an individual electrochemical cell

- Number and dimensions of positive and negative electrodes
- Number and dimensions of separators

# Self-discharge in practice

Tear-down of an individual electrochemical cell

- Number and dimensions of positive and negative electrodes
- Number and dimensions of separators
- Weight of each electrode (still soaked with electrolyte)

# Self-discharge in practice

Tear-down of an individual electrochemical cell

- Number and dimensions of positive and negative electrodes
- Number and dimensions of separators
- Weight of each electrode (still soaked with electrolyte)
- Weight of each electrode (after drying to remove electrolyte)



# Self-discharge in practice

Tear-down of an individual electrochemical cell

- Number and dimensions of positive and negative electrodes
- Number and dimensions of separators
- Weight of each electrode (still soaked with electrolyte)
- Weight of each electrode (after drying to remove electrolyte)
- Weight of each grid (after removing active materials)

# Self-discharge in practice


## Tear-down of an individual electrochemical cell

- Number and dimensions of positive and negative electrodes
- Number and dimensions of separators
- Weight of each electrode (still soaked with electrolyte)
- Weight of each electrode (after drying to remove electrolyte)
- Weight of each grid (after removing active materials)
- Estimation of the total volume of electrolyte in the cell

# Reference electrode

Study of each electrochemical reaction with the silver-silver sulfate reference electrode

To measure the potential of an individual working electrode, you must combine it with a reference electrode to form a galvanic cell.





# Reference electrode

Study of each electrochemical reaction with the silver-silver sulfate reference electrode

To measure the potential of an individual working electrode, you must combine it with a reference electrode to form a galvanic cell.

## Positive electrode as working electrode




## Reference electrode




Study of each electrochemical reaction with the silver-silver sulfate reference electrode

To measure the potential of an individual working electrode, you must combine it with a reference electrode to form a galvanic cell.

### Positive electrode as working electrode



### Negative electrode as working electrode



# Reference electrode

Impact of the reference electrode on the Butler-Volmer model of the negative electrode

The current density of charge transfer is described by the Butler-Volmer equation:

$$i = i_0 \left\{ \exp \left[ (1 - \alpha) \frac{2F}{RT^\circ} (\Delta\phi - \Delta\phi^0) \right] - \exp \left[ -\alpha \frac{2F}{RT^\circ} (\Delta\phi - \Delta\phi^0) \right] \right\}$$

with the exchange current density

$$i_0 = \frac{nFk_0}{\gamma_{\ddagger}} a_{\text{H}_2\text{SO}_4, \text{ref}}^{1-\alpha} a_{\text{H}_2\text{SO}_4}^{\alpha}$$

and the equilibrium potential at the reference temperature from the Nernst equation:

$$\Delta\phi_{\text{Pb}}^0(T^\circ) = \frac{\mu_{\text{PbSO}_4}^0 - \mu_{\text{Ag}_2\text{SO}_4}^0}{2F} - \frac{RT^\circ}{2F} \ln \left( \frac{a_{\text{H}_2\text{SO}_4}}{a_{\text{H}_2\text{SO}_4, \text{ref}}} \right)$$

# Working electrode

## Impact of temperature on current density and equilibrium voltage

The Arrhenius equation gives the dependence of the rate constant on  $T$

$$k_0 = k_0^\circ \exp\left(-\frac{\Delta\bar{G}_\ddagger}{RT}\right)$$

# Working electrode

## Impact of temperature on current density and equilibrium voltage

The Arrhenius equation gives the dependence of the rate constant on  $T$

$$k_0 = k_0^\circ \exp\left(-\frac{\Delta\bar{G}_\ddagger}{RT}\right)$$

The Taylor polynomial of degree 2 for the equilibrium potential according to  $T^\circ$

$$\Delta\phi^0(T) = \Delta\phi^0(T^\circ) + (T - T^\circ) \left(\frac{\partial\Delta\phi^0}{\partial T}\right)_p(T^\circ) + \frac{1}{2}(T - T^\circ)^2 \left(\frac{\partial^2\Delta\phi^0}{\partial T^2}\right)_p(T^\circ)$$

allows to estimate the equilibrium potential for any temperature value  $T \neq T^\circ$  from the entropy and heat capacity at constant pressure (isobaric process)

$$\Delta\phi^0(T) = \frac{\Delta\bar{G}^0(T^\circ)}{nF} - (T - T^\circ) \frac{\Delta\bar{S}^0(T^\circ)}{nF} - (T - T^\circ)^2 \frac{\Delta\bar{C}_p^0(T^\circ)}{2nFT}$$

# Working porous electrode

## Electroneutrality and conservation of charge

The porous electrodes of lead-acid batteries are made of two phases:

- a solid phase (Pb at the negative electrode and  $\text{PbO}_2$  at the positive electrode),
- a liquid phase (electrolyte).

# Working porous electrode

## Electroneutrality and conservation of charge

The porous electrodes of lead-acid batteries are made of two phases:

- a solid phase (Pb at the negative electrode and  $\text{PbO}_2$  at the positive electrode),
- a liquid phase (electrolyte).

This approach is simplistic as the electrodes are also made of binders (electrical insulators) and conductive additives, but allows to consider that the whole volume of the electrode is conductive with two different types of conduction according to the phases:

- electronic in the solid phase (exclusively metallic), symbolized by the current  $i_s$ ,
- ionic in the liquid phase (electrolyte), symbolized by the current  $i_l$ .

# Working porous electrode

## Electroneutrality and conservation of charge

The porous electrodes of lead-acid batteries are made of two phases:

- a solid phase (Pb at the negative electrode and  $\text{PbO}_2$  at the positive electrode),
- a liquid phase (electrolyte).

This approach is simplistic as the electrodes are also made of binders (electrical insulators) and conductive additives, but allows to consider that the whole volume of the electrode is conductive with two different types of conduction according to the phases:

- electronic in the solid phase (exclusively metallic), symbolized by the current  $i_s$ ,
- ionic in the liquid phase (electrolyte), symbolized by the current  $i_l$ .

**Electroneutrality (the double layer being negligible in volume)**

Charges leaving the porous matrix of the electrode must pass into the solution and reciprocally:

$$\nabla \cdot i_s + \nabla \cdot i_l = 0$$

# Working porous electrode

Kinetics and electrostatics are two sides of the same coin

The current per unit volume of the electrode  $\nabla \cdot i_l$ , transferred from the matrix to the solution, is involved either in faradaic reactions

$$\nabla \cdot i_l = A \sum_{j=1}^n i_j$$

where  $A$  is the specific interfacial area ( $\text{m}^{-1}$ ),  $\sum_{j=1}^n i_j$  the sum of the current densities of all faradaic processes  $j$  involved ( $\text{A m}^{-2}$ )

# Working porous electrode

Kinetics and electrostatics are two sides of the same coin

The current per unit volume of the electrode  $\nabla \cdot i_l$ , transferred from the matrix to the solution, is involved either in faradaic reactions or in double-layer charging:

$$\nabla \cdot i_l = A \sum_{j=1}^n i_j + \frac{d}{dt} (A q_{dl})$$

where  $A$  is the specific interfacial area ( $\text{m}^{-1}$ ),  $\sum_{j=1}^n i_j$  the sum of the current densities of all faradaic processes  $j$  involved ( $\text{A m}^{-2}$ ) and  $q_{dl}$  the surface charge density on the electrode side of the double layer ( $\text{C m}^{-2}$ ).

# Working porous electrode

Kinetics and electrostatics are two sides of the same coin

The current per unit volume of the electrode  $\nabla \cdot i_l$ , transferred from the matrix to the solution, is involved either in faradaic reactions or in double-layer charging:

$$\nabla \cdot i_l = A \sum_{j=1}^n i_j + \frac{d}{dt} (A q_{dl})$$

where  $A$  is the specific interfacial area ( $\text{m}^{-1}$ ),  $\sum_{j=1}^n i_j$  the sum of the current densities of all faradaic processes  $j$  involved ( $\text{A m}^{-2}$ ) and  $q_{dl}$  the surface charge density on the electrode side of the double layer ( $\text{C m}^{-2}$ ).

$$q_{dl} = C_{dl} \cdot \frac{d\Delta\phi}{dt} + \Delta\phi \cdot \frac{dC_{dl}}{dt}$$

where  $C_{dl}$  is the double layer capacity per unit area of the electrode ( $\text{F m}^{-2}$ ).

# Outline

- 1 Introduction
- 2 Self-discharge of lead-acid cells
- 3 Modeling self-discharge of a lead-acid cell**
  - Model equations
  - Model validation
  - Model improvements
- 4 Conclusion



# Model equations

Self-discharge means no charge transferred

In open circuit, no current flows, neither electronically ( $\nabla \cdot i_s = 0$ ), nor ionically:

$$\nabla \cdot i_l = A \sum_{j=1}^n i_j + \frac{d}{dt} (A q_{dl}) = 0$$

# Model equations

Self-discharge means no charge transferred

In open circuit, no current flows, neither electronically ( $\nabla \cdot i_s = 0$ ), nor ionically:

$$\nabla \cdot i_l = A \sum_{j=1}^n i_j + \frac{d}{dt} (A q_{dl}) = 0$$

Assuming two faradaic processes:

- discharge of the electrode active material with the primary current  $i_p$
- hydrolysis of water contained in electrolyte with the gassing current  $i_g$

and a constant double layer capacity per unit area of the electrode ( $\frac{dC_{dl}}{dt} = 0$ )


$$\frac{d\Delta\phi}{dt} = -\frac{i_p + i_g}{C_{dl}}$$

# Model equations

Self-discharge means sulfuric acid consumption and dilution

Reducing self-discharge to **sulfuric acid** consumption works for the negative:

## Negative electrode





# Model equations

Self-discharge means sulfuric acid consumption and dilution



Reducing self-discharge to **sulfuric acid** consumption works for the negative:

## Negative electrode



but is not sufficient for the positive, producing and consuming **water**:

## Positive electrode




# Model equations

Self-discharge means sulfuric acid consumption and dilution



Reducing self-discharge to **sulfuric acid** consumption works for the negative:

## Negative electrode



but is not sufficient for the positive, producing and consuming **water**:

## Positive electrode



$$\forall i \in \{\text{H}_2\text{O}, \text{H}_2\text{SO}_4\}, j \in \{\text{p}, \text{g}\}, k \in \{\text{pos}, \text{neg}\}, \quad \frac{dn_i}{dt} = - \sum_{j,k} \frac{s_{i,j,k} N_k S_k}{n_{j,k} F} i_{j,k}$$

# Model equations

A system of 7 ordinary differential equations (2 for each electrode and 3 for the electrolytes)

Electrode  $k$

$$\frac{d\Delta\phi_k}{dt} = -\frac{1}{C_{dl,k}} \sum_j i_{j,k}$$

$$\frac{dQ_k}{dt} = -s_{p,k} N_k S_k i_{p,k}$$

$$SOC_k = \frac{Q_k}{\max(Q_k)}$$

# Model equations

A system of 7 ordinary differential equations (2 for each electrode and 3 for the electrolytes)

Electrode  $k$

$$\frac{d\Delta\phi_k}{dt} = -\frac{1}{C_{dl,k}} \sum_j i_{j,k}$$

$$\frac{dQ_k}{dt} = -s_{p,k} N_k S_k i_{p,k}$$

$$SOC_k = \frac{Q_k}{\max(Q_k)}$$

The cell  $SOC$  corresponds to the minimum value of each electrode  $SOC_k$ :

$$SOC = \min\left(\max(\min(SOC_k), 0), 1\right)$$

# Model equations

A system of 7 ordinary differential equations (2 for each electrode and 3 for the electrolytes)

## Electrode $k$

$$\frac{d\Delta\phi_k}{dt} = -\frac{1}{C_{dl,k}} \sum_j i_{j,k}$$

$$\frac{dQ_k}{dt} = -s_{p,k} N_k S_k i_{p,k}$$

$$SOC_k = \frac{Q_k}{\max(Q_k)}$$

## Bulk electrolyte

$$\frac{dn_{H_2O}}{dt} = -\sum_{j,k} \frac{s_{H_2O,j,k} N_k S_k}{n_{j,k} F} i_{j,k}$$

$$\frac{dn_{H_2SO_4}}{dt} = -\sum_{j,k} \frac{s_{H_2SO_4,j,k} N_k S_k}{n_{j,k} F} i_{j,k}$$

$$m = \frac{1000 n_{H_2SO_4}}{M_{H_2O} n_{H_2O}}$$

The cell  $SOC$  corresponds to the minimum value of each electrode  $SOC_k$ :

$$SOC = \min(\max(\min(SOC_k), 0), 1)$$

# Model equations

A system of 7 ordinary differential equations (2 for each electrode and 3 for the electrolytes)

## Electrode $k$

$$\frac{d\Delta\phi_k}{dt} = -\frac{1}{C_{dl,k}} \sum_j i_{j,k}$$

$$\frac{dQ_k}{dt} = -s_{p,k} N_k S_k i_{p,k}$$

$$SOC_k = \frac{Q_k}{\max(Q_k)}$$

The cell  $SOC$  corresponds to the minimum value of each electrode  $SOC_k$ :

$$SOC = \min\left(\max(\min(SOC_k), 0), 1\right)$$

## Bulk electrolyte

$$\frac{dn_{H_2O}}{dt} = -\sum_{j,k} \frac{s_{H_2O,j,k} N_k S_k}{n_{j,k} F} i_{j,k}$$

$$\frac{dn_{H_2SO_4}}{dt} = -\sum_{j,k} \frac{s_{H_2SO_4,j,k} N_k S_k}{n_{j,k} F} i_{j,k}$$

$$m = \frac{1000 n_{H_2SO_4}}{M_{H_2O} n_{H_2O}}$$


## Reference electrolyte

$$\frac{dm_{ref}}{dt} = \frac{D_{ref}}{S_{ref}} (m - m_{ref})$$

# Model validation with experimental data

Electrode voltage and SOC during 49 days at 25 °C, 34 days at 35 °C, and 16 days at 45 °C


## Positive electrode voltage




# Model validation with experimental data

Electrode voltage and SOC during 49 days at 25 °C, 34 days at 35 °C, and 16 days at 45 °C

## Positive electrode voltage




## Negative electrode voltage




# Model validation with experimental data

Electrode voltage and SOC during 49 days at 25 °C, 34 days at 35 °C, and 16 days at 45 °C


## Positive electrode voltage



## Negative electrode voltage




## State of charge




# Model validation with experimental data

Electrode voltage and SOC during 49 days at 25 °C, 34 days at 35 °C, and 16 days at 45 °C


## Positive electrode voltage



## Negative electrode voltage



## State of charge




- The positive electrode polarization is much higher than the negative one.


# Model validation with experimental data

Electrode voltage and SOC during 49 days at 25 °C, 34 days at 35 °C, and 16 days at 45 °C


## Positive electrode voltage



## Negative electrode voltage



## State of charge




- The positive electrode polarization is much higher than the negative one.
- The positive electrode voltage decreases faster than the negative one.


# Model validation with experimental data

Electrode voltage and SOC during 49 days at 25 °C, 34 days at 35 °C, and 16 days at 45 °C


## Positive electrode voltage



## Negative electrode voltage



## State of charge




- The positive electrode polarization is much higher than the negative one.
- The positive electrode voltage decreases faster than the negative one.
- The positive electrode SOC decreases slower than the negative one.

# Model validation with experimental data

Bulk and reference electrolytes during 49 days at 25 °C, 34 days at 35 °C, and 16 days at 45 °C


## Bulk electrolyte density




# Model validation with experimental data

Bulk and reference electrolytes during 49 days at 25 °C, 34 days at 35 °C, and 16 days at 45 °C

## Bulk electrolyte density




## Bulk and ref molalities




# Model validation with experimental data

Bulk and reference electrolytes during 49 days at 25 °C, 34 days at 35 °C, and 16 days at 45 °C


## Bulk electrolyte density



## Bulk and ref molalities




## Moles of water and acid




# Model validation with experimental data

Bulk and reference electrolytes during 49 days at 25 °C, 34 days at 35 °C, and 16 days at 45 °C


## Bulk electrolyte density



## Bulk and ref molalities



## Moles of water and acid




- Relative errors of density and voltages are very low ( $\pm 0.3\%$ ).


# Model validation with experimental data

Bulk and reference electrolytes during 49 days at 25 °C, 34 days at 35 °C, and 16 days at 45 °C


## Bulk electrolyte density



## Bulk and ref molalities



## Moles of water and acid




- Relative errors of density and voltages are very low ( $\pm 0.3\%$ ).
- Diffusion of species from the bulk is very slow but non negligible.


# Model validation with experimental data

Bulk and reference electrolytes during 49 days at 25 °C, 34 days at 35 °C, and 16 days at 45 °C


## Bulk electrolyte density



## Bulk and ref molalities



## Moles of water and acid




- Relative errors of density and voltages are very low ( $\pm 0.3\%$ ).
- Diffusion of species from the bulk is very slow but non negligible.
- The model shows how the acid is diluted by water production.

# Model extrapolation

Simulating the impact of a one-year selfdischarge at 25 °C on electrolyte density, cell voltage and SOC


## Electrolyte density




# Model extrapolation

Simulating the impact of a one-year selfdischarge at 25 °C on electrolyte density, cell voltage and SOC

## Electrolyte density




## Cell voltage




# Model extrapolation

Simulating the impact of a one-year selfdischarge at 25 °C on electrolyte density, cell voltage and SOC


## Electrolyte density



## Cell voltage




## Cell SOC




# Model extrapolation

Simulating the impact of a one-year selfdischarge at 25 °C on electrolyte density, cell voltage and SOC


## Electrolyte density



## Cell voltage



## Cell SOC



Thermodynamics and kinetics make the electrolyte density, cell voltage, and SOC decrease exponentially, showing that the lower the SOC, the lower the selfdischarge phenomenon.

# Model improvements

Electrolyte density measurement issues, long-term selfdischarge at 40 °C, and sealed technologies

- Measurements from the electrolyte reserve located above the electrodes may lead to lower density values than the actual ones inside the pores.

# Model improvements

Electrolyte density measurement issues, long-term selfdischarge at 40 °C, and sealed technologies

- Measurements from the electrolyte reserve located above the electrodes may lead to lower density values than the actual ones inside the pores.
- Measurements with a densimeter have to be done in accordance with the allowed temperature range (measurements above 40 °C may be inaccurate).

# Model improvements

Electrolyte density measurement issues, long-term selfdischarge at 40 °C, and sealed technologies

- Measurements from the electrolyte reserve located above the electrodes may lead to lower density values than the actual ones inside the pores.
- Measurements with a densimeter have to be done in accordance with the allowed temperature range (measurements above 40 °C may be inaccurate).
- A long-term self-discharge at 40 °C has been started recently to:
  - experimentally validate the model beyond one-month,
  - potentially add the impact of corrosion and loss of water by evaporation, if necessary.

# Model improvements

Electrolyte density measurement issues, long-term selfdischarge at 40 °C, and sealed technologies

- Measurements from the electrolyte reserve located above the electrodes may lead to lower density values than the actual ones inside the pores.
- Measurements with a densimeter have to be done in accordance with the allowed temperature range (measurements above 40 °C may be inaccurate).
- A long-term self-discharge at 40 °C has been started recently to:
  - experimentally validate the model beyond one-month,
  - potentially add the impact of corrosion and loss of water by evaporation, if necessary.
- The model should be applied on sealed lead-acid cells as well.

# Outline

- 1 Introduction
- 2 Self-discharge of lead-acid cells
- 3 Modeling self-discharge of a lead-acid cell
- 4 Conclusion**
  - What we have learned
  - What should be done next
  - Acknowledgments

# What we have learned

- Self-discharge has an obvious impact on operational performance and safety.

## What we have learned

- Self-discharge has an obvious impact on operational performance and safety.
- Self-discharge involves many processes that are uneasy to isolate and identify.

## What we have learned

- Self-discharge has an obvious impact on operational performance and safety.
- Self-discharge involves many processes that are uneasy to isolate and identify.
- Self-discharge of lead-acid batteries is finally not so well-known.

# What we have learned

- Self-discharge has an obvious impact on operational performance and safety.
- Self-discharge involves many processes that are uneasy to isolate and identify.
- Self-discharge of lead-acid batteries is finally not so well-known.
- Efficient modeling of self-discharge requires to cover the complete value chain:
  - Experimental work,
  - Data collection and analysis,
  - Model development, parameter identification, and validation.

# What should be done next

- If you don't know precisely what happens inside one cell, when there is no current going through it, do you sincerely believe you could drop that step and jump directly to the modeling of battery (dis)charge with more success?

## What should be done next

- If you don't know precisely what happens inside one cell, when there is no current going through it, do you sincerely believe you could drop that step and jump directly to the modeling of battery (dis)charge with more success?
- "It is better to do the right problem the wrong way than the wrong problem the right way." R. Hamming



*Richard Hamming  
(1915–1998)*







