



HAL
open science

Solubility of uranium oxide in ternary aluminosilicate glass melts

Olivier Podda, Laurent Tissandier, Annabelle Laplace-Ploquin, Etienne Deloule

► **To cite this version:**

Olivier Podda, Laurent Tissandier, Annabelle Laplace-Ploquin, Etienne Deloule. Solubility of uranium oxide in ternary aluminosilicate glass melts. ICG2022 - 26th International Congress on Glass, ICG, Jul 2022, Berlin, Germany. cea-03722316

HAL Id: cea-03722316

<https://cea.hal.science/cea-03722316>

Submitted on 13 Jul 2022

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

Solubility of uranium oxide in ternary aluminosilicate glass melts

Olivier Podda^{1*}, Laurent Tissandier², Annabelle Laplace¹, Etienne Deloule²

¹ CEA, DES, ISEC, DE2D, Laboratoire de Développement des Matrices de Conditionnement, Univ. Montpellier, Marcoule, France

² Université de Lorraine, CNRS, CRPG, 54500 Vandœuvre-lès-Nancy, France

*olivier.podda@cea.fr

The immobilization of highly radioactive waste using vitrification process has been in application since many decades [1]. This process can reduce the potential for radionuclides migration or dispersion [2] by chemical incorporation into the structure of a glass matrix in order to trap radionuclides. This process is now under investigation for conditioning Intermediate Level Waste – Long Life (ILW-LL) using aluminosilicate glasses as host matrices. The vitrification must be able to maintain, within a certain range of composition and redox potential, the actinides solubility. It is known that uranium chemistry is complex in glass-forming systems due to the presence of many oxidation states (VI, V, IV), each of them having a specific solubility in melts.

The aim of this work is to determine and model uranium solubility and its oxidation states as a function of the glass melt composition and oxidoreduction potential (oxygen fugacity, from $10^{-0.7}$ atm to 10^{-16} atm). The ternary $\text{SiO}_2\text{-Al}_2\text{O}_3\text{-CaO}$ (CAS) and $\text{SiO}_2\text{-Al}_2\text{O}_3\text{-MgO}$ (MAS) systems are studied. Different compositions are synthesized by modifying the Al content for each ternary system. Uranium is added in excess in order to reach an equilibrium between the melt and uranium oxide crystals.




Figure 1. Total uranium content reported as weight% UO_2 as the function of oxygen fugacities for CAS system. Elaboration temperature was 1400°C . Error bars represent the standard deviation based on reproducibility of 30 EDS analyses for each samples.

This presentation will give results on the behaviour of uranium over a large redox range. The results of uranium solubility (SEM/EDS) as a function of oxygen fugacity as well as a function of Al_2O_3 content will be presented (example on Figure 1). Analyses of uranium oxide crystals (XRD) were carried out. The proportion of uranium oxidation states was determined by XANES while their different structures were analysed by EXAFS. Hypotheses on the differences in behaviour between the two systems CAS and MAS will be formulated.

References

- [1] P. Colombo; *Current Opinion in Solid State and Materials Science*, 7(3), 2003, 225-239.
- [2] M.I. Ojovan; An introduction to nuclear waste immobilisation, Elsevier 2019