



**HAL**  
open science

## Corrosion protection of copper and bronze statuary by carboxylates-doped sol-gel coatings

Silvia Lob, Thu-Hoa Tran-Thi, Aurélia Azema, Christine Richter, Delphine D.  
Neff

► **To cite this version:**

Silvia Lob, Thu-Hoa Tran-Thi, Aurélia Azema, Christine Richter, Delphine D. Neff. Corrosion protection of copper and bronze statuary by carboxylates-doped sol-gel coatings. EuroCorr 2022 - the European Corrosion Congress 2022, Aug 2022, Berlin, Germany. cea-03766424

**HAL Id: cea-03766424**

**<https://cea.hal.science/cea-03766424v1>**

Submitted on 1 Sep 2022

**HAL** is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

## Corrosion protection of copper and bronze statuary by carboxylates-doped sol-gel coatings

*S. Lob, CY Cergy Paris Université; Thu-Hoa Tran-Thi, CNRS Paris, Aurélia Azema, LRMH Paris, Christine Richter, CY Cergy Paris Université, Delphine Neff, CEA Paris*

### WP 21 : Corrosion of Archaeological and Historical Artefacts

This study investigates innovative non-toxic carboxylate protection treatments against corrosion of statuary bronze artefacts. Over the past decades, research has focused on conserving these objects exposed to the atmosphere with special attention on the preservation of corrosion layers (CL). Recent studies have reported the efficiency of long chain carboxylates in protecting copper patina from subsequent deterioration<sup>1</sup>. However, this penetration process becomes more difficult when applied by brush on site and remains a main issue. Therefore, we present a new method to address this matter. In this study, the statuary surface layer is coated with an additional silicon layer produced via the sol-gel process<sup>2</sup> using a dip-coating technique, with a tetra-alkoxysilane (TMOS) precursor and containing high carboxylate concentration. The carboxylic acids used display short hydrocarbon chains with 7, 8 and 10 carbons. Experiments are conducted on century old copper samples exposed to weathering interactions.

A multi-scale analytical approach is undertaken to better understand the mechanisms and physicochemical interactions between the organic treatment and the CL formed on the surface of the historical copper. The treatment's penetration is also investigated on samples exposed outside for one year under atmospheric condition, to measure effects of natural weathering and treatment resistivity.

In this work, we demonstrate the efficiency of silicon layer doped with short chain carboxylates as an efficient barrier layer to protect copper from corrosion. Results show that all carboxylic acids allow the formation of an organometallic complex at the surface of the CL with a surface coverage dependent on the acid. All the silicon layers doped with carboxylic acids are transparent, with a thickness up to 4  $\mu\text{m}$ , and have no impact on the colour of the CL's surfaces. Moreover, the SEM-EDS and Raman studies of the CL's cross sections show the penetration of both the sol-gel and the carboxylic acid/copper carboxylate mix deep into the external CL of brochantite.

1. Rocca, Steinmetz, *Corros. Sci.* **43**, 891-902 (2001)

2. Wang, Bierwagen, *Porg. Org. Coatings* **64**, 327-338 (2009).