



HAL
open science

Modeling the uranium solubility in aluminosilicate glass melts

Olivier Podda, Laurent Tissandier, Annabelle Laplace-Ploquin, Etienne Deloule

► To cite this version:

Olivier Podda, Laurent Tissandier, Annabelle Laplace-Ploquin, Etienne Deloule. Modeling the uranium solubility in aluminosilicate glass melts. DEM 2021 - International Conference on Decommissioning Challenges: Industrial Reality, Lessons Learned and Prospects, SFEN, Sep 2021, Avignon, France. <cea-03773981>

HAL Id: cea-03773981

<https://cea.hal.science/cea-03773981v1>

Submitted on 12 Sep 2022

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire HAL, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.



HAL Authorization

Modeling the uranium solubility in aluminosilicate glass melts

Olivier Podda^{1,2*}, Laurent Tissandier², Annabelle Laplace¹, Etienne Deloule²

¹CEA, DES, ISEC, DE2D, Laboratoire de Développement des Matrices de Conditionnement, Univ. Montpellier, Marcoule, France

²Université de Lorraine, CNRS, CRPG, 54500 Vandoeuvre les Nancy, France

*Corresponding Author, E-mail: olivier.podda@cea.fr

KEYWORDS: *Uranium, solubility, aluminosilicate glass melt, redox reaction*

Abstract

In the frame of the development of nuclear waste vitrification processes, special attention is paid to solid waste containing metals contaminated with actinides, and in particular with uranium (production waste, decommissioning waste, for example). Whether to decontaminate the metal phase or to vitrify the actinides, the objective is to solubilize the actinides in the vitreous phase. Nevertheless, oxidation-reduction reactions between the glass and the metallic phase can modify the composition of the melt. The vitrification must be able to maintain, within a certain range of compositions and redox potential, the actinides solubility. It is known that uranium solubility is highly dependent on its oxidation states (VI, V, IV) [1]. Indeed, Uranium VI is the most soluble oxidation state while uranium IV is the least soluble.

The aim of this work is to determine and model uranium solubility and its oxidation states as a function of the glass melt oxidoreduction potential and composition. To do so, two parameters; which are oxygen fugacity and glass composition; are evaluated. In this work, the ternary SiO₂-Al₂O₃-CaO and SiO₂-Al₂O₃-MgO systems are studied. For each one, different compositions are synthesized while keeping the ratio Si/Ca and Si/Mg constant. Uranium is introduced into the glass in its most soluble form, i.e. U(VI). The redox of the glass is then modified in a muffle furnace at 1400°C with a CO/CO₂ gas mixture up to the equilibrium. The quenched samples were then analyzed by SEM and EDS to determine the solubility of uranium.

This paper presents our results on the uranium solubility in aluminosilicate glasses. The evolution of the uranium solubility as a function of the oxygen fugacity and for different glass compositions is exposed.

[1] Schreiber, H. D. (1983). The chemistry of uranium in glass-forming aluminosilicate melts. *Journal of the Less Common Metals*, 91(1), 129-147.