

Understanding the behaviour of magnesium potassium phosphate cements under alkaline environment

Celine Cau Dit Coumes, Laura Diaz Caselles, Gabriel Poras, Angélique Rousselet, Adel Mesbah, Valérie Montouillout

► To cite this version:

Celine Cau Dit Coumes, Laura Diaz Caselles, Gabriel Poras, Angélique Rousselet, Adel Mesbah, et al.. Understanding the behaviour of magnesium potassium phosphate cements under alkaline environment. 2nd International Conference on Innovation in Low-Carbon Cement & Concrete Technology, Jul 2024, Londres, United Kingdom. cea-04665173

HAL Id: cea-04665173 https://cea.hal.science/cea-04665173v1

Submitted on 31 Jul2024

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers. L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.



UNDERSTANDING THE BEHAVIOUR OF MAGNESIUM POTASSIUM PHOSPHATE CEMENTS UNDER ALKALINE ENVIRONMENT

Céline CAU DIT COUMES ^{1,*}, Laura DIAZ CASELLES ¹, Gabriel PORAS ¹, Angélique ROUSSELET ², Adel MESBAH ³, Valérie MONTOUILLOUT ⁴

¹ CEA, DES, ISEC, DPME, SEME, LFCM, Univ Montpellier, Marcoule, France
² CEA, DES, ISAS, DRMP, S2CM, LECBA, Université Paris-Saclay, Gif-sur-Yvette, France
³ Univ Lyon, Université Lyon 1, IRCELYON, UMR5256, CNRS, Villeurbanne, France
⁴ CNRS, CEMHTI UPR3079, Univ. Orléans, Orléans, France
*Corresponding author: celine.cau-dit-coumes@cea.fr
Presenting author: Céline CAU DIT COUMES

ABSTRACT

Magnesium potassium phosphate cements (MKPCs) are clinker-free acid-base binders that form through the reaction between magnesium oxide (MgO) and potassium dihydrogen phosphate (KH₂PO₄). In contact with water, dissolution and precipitation take place, mainly yielding K-struvite (MgKPO₄.6H₂O). MKPCs are of interest for patch repair work thanks to their fast setting and good adherence to old Portland cement (PC)-based concrete, but are also investigated for bioengineering, 3D printing and solidification / stabilization of hazardous waste. However, the understanding of their long-term evolution is still limited. Hence, this work aims at investigating the degradation mechanisms of MKPC paste under alkaline environment by considering two configurations: MKPC paste (*i*) in close contact with PC paste, or (*ii*) leached by an alkaline solution mimicking the pore solution of the PC paste.

MKPC (Mg/P molar ratio = 1) and PC pastes were prepared at a water-to-cement ratio of 0.51 and 0.4, respectively, and cured under endogenous conditions at 20°C for 28 d or 180 d. For the MKPC/PC paste interface study (*i*), two cylindrical samples were initially resaturated with their own synthetic pore solutions and maintained confined in a Hoek cell for 3 or 8 months. For the leaching study (*ii*), semi-dynamic leaching tests were carried out for 14 d and 170 d on MKPC monoliths using an alkaline solution which was periodically renewed to avoid accumulation of dissolved species. Leachates were analysed by ICP-AES. In both kinds of experiments, post-mortem characterization of the solids was performed using XRD, SEM/EDS and ³¹P MAS-NMR.

Leaching induced a decrease in the content of crystalline K-struvite, as well as the precipitation of Cadeficient hydroxyapatite (CDHA), brucite and possibly magnesium silicate hydrates. A thin layer of CDHA was also evidenced at the MKPC/PC paste interface and could explain the good bonding between these two materials.

<u>Acknowledgements</u>: This project has received funding from the European Union's Horizon 2020 research and innovation programme for Nuclear Fission and Radiation Protection Research (Call NFRP-2019-2020) under grant agreement No. 945098 (PREDIS).

KEYWORDS

Magnesium phosphate cement; Portland cement; Durability; Phase evolution; Leaching