



HAL
open science

New lithium salts derived from naphthalene: toward carbonate-based single-ion polymer electrolytes

Chloé Farina, Laurent Bernard, Matthieu Landa, Nicolas Leconte, Lionel Picard

► To cite this version:

Chloé Farina, Laurent Bernard, Matthieu Landa, Nicolas Leconte, Lionel Picard. New lithium salts derived from naphthalene: toward carbonate-based single-ion polymer electrolytes. Battery 2030+ Annual Conference: Sustainable batteries of the future, May 2024, Grenoble, France. , 2024. cea-04706841

HAL Id: cea-04706841

<https://cea.hal.science/cea-04706841v1>

Submitted on 23 Sep 2024

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

Chloé FARINA¹, Laurent BERNARD¹, Matthieu LANDA¹, Nicolas LECONTE², Lionel PICARD¹

¹ Univ. Grenoble Alpes, CEA, Liten, 38000 Grenoble, France - E-mail: chloe.farina@cea.fr

² Univ. Grenoble Alpes, Department of Molecular Chemistry, 38000 Grenoble, France




AGENCE
INNOVATION
DÉFENSE



Grenoble
ÉCOLE DOCTORALE I-MEP2



Context




Strategy: substitution of liquid electrolytes with solid materials

3 different classes of solid electrolytes: oxides, sulfides, and **polymers**

Strengths	Weaknesses
<ul style="list-style-type: none"> Lightweight Interface properties with active materials Adaptation to electrode volume changes Easy to process 	<ul style="list-style-type: none"> Ionic conductivity at room temperature Mechanical properties

State-of-the art: PEO-like polymer electrolytes

- Dissolution of lithium salts in a polymer matrix
- Conductivity via the **segmental motion of polymer chains and diffusion** [2]



❖ PEO ELECTROLYTES [3,4]


Strengths

- Ionic conductivity about 1 mS.cm⁻¹ at 80°C
- Low glass-transition temperature ($T_g = -60^\circ\text{C}$)

Weaknesses

- Non-conductive crystalline phases ($T_f = 60^\circ\text{C}$)
- Strong interactions between Li⁺ and polymer chains
- Limited to low voltage cathode materials (stable up to 4V vs .Li⁺/Li₀)

➔ Study of other families of polymer electrolytes




Objectives

- Development of **stable high voltage polymer electrolytes** for high energy density batteries
- **Single-ion polycarbonate** synthesis (PTMC derivative) by covalently **grafting Li⁺ counter-ions** on polymer chains
- Synthesis and electrochemical characterization of **new model salts**

High voltage polymer electrolyte


❖ POLY(TRIMETHYLENE CARBONATE) (PTMC)

- Amorphous polymer: $T_g = -20^\circ\text{C}$ [5]
- Ionic conductivity is **mainly due to Li⁺ mobility**
→ $t_{\text{Li}^+} \approx 0,8$ [6]
- **Electrochemical stability up to 4.8V** vs. Li⁺/Li₀ [5]
→ High voltage cathode compatibility




Carbonate-based single-ion polymer electrolytes


Classic single-ion polymer architecture [7]



This work




❖ ELECTROCHEMICAL CHARACTERIZATION OF NEW LITHIUM SALTS




Single-ion polymer strategy

Classic polymer electrolyte



Single-ion polymer electrolyte



Covalent grafting of anions on polymer chains

Charge accumulation

✓ Only Li⁺ ions move via the segmental motion of polymer chains ($t_{\text{Li}^+} \approx 1$) [6]

Conclusions and perspectives

- Preparation of **new polymer electrolyte systems** with **weakly coordinating lithium salts** derived from naphthalene and electrochemical characterizations
- Development of a **versatile synthesis method** for **single-ion functionalized cyclic carbonate monomers**
- Study of the **copolymerization** of cyclic carbonate monomers and **single-ion functionalized cyclic carbonate monomers**

References

[1] J. B. Goodenough, *Nat. Electron.*, **2018**, 1, 204–204.

[2] Y. An, *et al. Small*, **2022**, 18, 2103617.

[3] J. Mindemark, *et al. Prog. Polym. Sci.*, **2018**, 81, 114–143.

[4] A. Maurel, *et al. J. Electrochem. Soc.* **2020**, 167, 070536.

[5] T. Clement (2021). *Copolymères en peigne à greffons éthers et carbonates: du design macromoléculaire à leur utilisation comme électrolyte de batterie au lithium* [Doctoral thesis, Univ. Grenoble Alpes]

[6] M. Irfan, *et al. J. Power Sources* **2021**, 486, 229378.

[7] R. Bouchet, *et al. Nature Mater* **2013**, 12 (5), 452–457.