



HAL
open science

Development and characterization of new families of organic alkaline salts for Charge Transfer Complexes in battery applications

Romain Kunert, Noëline Tessier, Lionel Picard, Laurent Bernard

► **To cite this version:**

Romain Kunert, Noëline Tessier, Lionel Picard, Laurent Bernard. Development and characterization of new families of organic alkaline salts for Charge Transfer Complexes in battery applications. ISPE 18 - 18th International Symposium on Polymer Electrolytes, Jun 2024, Langkawi, Kuah, Malaysia. cea-04719772


HAL Id: cea-04719772

<https://cea.hal.science/cea-04719772v1>

Submitted on 3 Oct 2024

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.



Development and characterization of new families of organic alkaline salts for Charge Transfer Complexes in battery applications


Commissariat à l'énergie atomique et aux énergies alternatives, Grenoble (France)

KUNERT Romain / TESSIER Noëline / BERNARD Laurent / PICARD Lionel





Some numbers



- Global need of batteries for electric mobility:
 - Approx. **30% annual increase** for electric transportation
 - **135 to 250 million** electric vehicles in 2030 (30 millions currently)




- global market of **58 billion USD** (2022)
- expected to reach **293 billion USD** by 2032**

*Prevision of battery needs throughout 2030 (GWh)**



Li-ion technology




- Roadblocks to globalization:
 - ✓ Autonomy, wear and tear
 - ✗ Materials cost and **criticality**
 - Alternative Na/K technologies, LFP cathodes ...
 - ✗ **Safety hazards** (leakage, inflammable toxic electrolyte)







Solid-state batteries





- ✓ Performances: Li metal anode (energy density)
- ✓ Enhanced safety: reduced flammability, dendrites growth
- Solid Electrolytes:
 - Inorganic: sulfurs, oxides
 - Composites: Polymer matrix + inorganic electrolyte
 - **Organic electrolytes**
- ✓ Tunable mechanical properties
- ✓ Cheaper and usually easier to process
- ✗ Limited electrochemical properties
 - Ionic conductivities ($\sigma_{PEO} = 10^{-6} \text{ S.cm}^{-1}$ at 25°C)
 - Li transference number ($t_{Li^+,PEO} = 0,2$)

Charge-Transfer Complexes



Charge-Transfer Complexes (ionic materials)




- ✓ Super-ionic conductivity ($\sigma > 10^{-3}$ S/cm at RT)
- ✓ Electrochemical stability
- ✗ No reproducibility
- ✗ Unclear conduction mechanism (interface polarity, segmental motion?)




Alternative CTC electrolyte systems (N. Tessier)


Donors




PNZ




TMB



HQ




TTF



DD


Acceptors



CA




BQ



TCNQ

Li salt



LiTFSI


- Standardized preparation and characterization of CTC electrolytes:
 - Mixing in tetrahydrofuran solvent, evaporation then reduced pressure drying (80°C, 48 h)
 - Impedance + Wagner polarization method to determine electronic/ionic conductivity




PNZ/TCNQ CTC



HQ/BQ/LiTFSI powders




Alternative CTC electrolyte systems (N. Tessier)




➤ Selected HQ/BQ system


- Alternative Li salts
- Different formulations
- Different material processes



	HQ/BQ	TTF/CA	PNZ/TCNQ	TMB/TCNQ	TMB/CA	DD/TCNQ
Conductivity	Ionic	Mixed ?	Ionic	Ionic	Electronic	Electronic
Value at RT (S.cm ⁻¹)	5.6x10⁻⁶	1.4x10 ⁻⁷	2.9x10 ⁻⁸	1.6x10 ⁻⁸	1.7x10 ⁻⁷	2.4x10 ⁻⁸



Alternative CTC electrolyte systems (N. Tessier)




➤ HQ/BQ derivatives (LiTFSI Li salt)

- Benzoquinone derivatives with increasingly electrowithdrawing substituents
- Modification of CTC orbitals: impact on ionic conductivity ?
- Investigated in theoretical calculations: charge transfer degree, dipolar moment (μ_{dip}), CTC band gap (E_g)...


	HQ/BQ	HQ/CA	HQ/BA	HQ/FA
σ : RT (S.cm ⁻¹)	1.0x10 ⁻⁸	1.0x10 ⁻⁷	3.0x10 ⁻⁸	5.0x10 ⁻⁸
σ : 80°C (S.cm ⁻¹)	2.5x10 ⁻⁶	6.4x10 ⁻⁶	1.7x10 ⁻⁵	1.5x10 ⁻⁷

- ✗ No direct correlation
- ✗ Confirmed in DFT calculations
- Different parameters: morphology studies

Single-ion conducting polymers




Binary-ion conductor



Mobile anions

- ✓ Low ionic selectivity ($t_{Li^+} \approx 0.2$)
- ✓ Low oxidation voltage (< 4 V)
- ✓ High cell polarization


Single-ion conductor




Immobile anions

- ✓ High ionic selectivity ($t_{Li^+} \approx 1$)
- ✓ High oxidation voltage (> 4 V)
- ✓ Resistance to dendrite growth


- Immobilized Li^+ anion partner
- ✗ Improvable ionic conductivities ($\sigma = 10^{-4}$ - 10^{-6} S/cm)




Single-ion CTCs



- Covalent grafting on **acceptor** or **donor** molecules of the CTC
- Expected high ionic selectivity ($t_{\text{Li}^+} \approx 1$) and electrochemical stability
- Investigation on the conduction mechanism of CTC electrolytes




Syntheses of modified chloranil salts



- Ideal organic platform to implant **anions** (TFSI derivative or fluoride-free malononitrile)
- ✓ Adaptable one-pot syntheses
- ✓ Possibility to reach bis-lithiated salts (better energy density ?)
- ✓ Na^+/K^+ cations incorporation for Na/K battery technologies
- ✓ More convenient and versatile formulation and processing to form CTC electrolytes

Syntheses of modified chloral salt







- Different alkaline bases (LiOH.H₂O, LiH), solvents, reagents introduction order.. allow for further optimization
- Purification through simple successive filtrations
- ✓ Products and purities verified through ⁷Li (Li salts), ¹³C, ¹⁹F (TFSI derivatives) NMR, ESI-MS(-) and FTIR spectroscopies




Impedance results (patent in preparation)

- Solid-state conductivities in polymer matrix
 - Reproducibility issues ($<10^{-8}$ to $5 \cdot 10^{-4}$ S.cm $^{-1}$)
 - Unclear behaviour under temperature
- Addition of sulfolane plasticizer (10 to 17% wt.)
 - Reproducible but limited conductivities
 - ✓ $\sigma > \mu\text{S.cm}^{-1}$ at RT for 3 alkaline ions (Li,Na,K)






Conclusion: functionalized chloranil acceptor



- ✓ Promising results for improvement
- ✗ Many components for optimization/understanding
 - Taking 1 polymer:
 - 4 different salts for 1 metal cation (Li or Na or K)
 - Polymer/acceptor salt ratio
 - Different preparations possible (solvents / annealing...)
 - Impact of plasticizer




Conclusion: functionalized chloranil acceptor



- ✓ Promising results for improvement
- ✗ Many components for optimization/understanding
 - Taking 1 polymer:
 - 4 different salts for 1 metal cation (Li or Na or K)
 - Polymer/acceptor salt ratio
 - Different preparations possible (solvents / annealing...)
 - Impact of plasticizer


➤ Functionalized polyphenylene polymers



Focus on one polymer system
for deep characterization




Functionalized polyphenylene polymer for single-ion CTCs (patent in preparation)





- Exact structures and syntheses to be protected in patent
- Characterized through NMR and FTIR spectroscopies
- ✗ Solubility issues: purification and processing difficulties
- Tested as single-ion polymers in CTC electrolytes with plasticizer



Functionalized polyphenylene polymer for single-ion CTCs (patent in preparation)



- Exact structures and syntheses to be protected in patent
- Characterized through NMR and FTIR spectroscopies
- ✗ Solubility issues: purification and processing difficulties
- Tested as single-ion polymers in CTC electrolytes with plasticizer



- ✓ Reproducible results
- ✓ Decent conductivities:
 1.10^{-5} S.cm⁻¹ at RT, 9.10^{-5} S.cm⁻¹ at 80°C
- Further characterizations on-going



Conclusion and perspectives

- ✓ Mixed but promising results for improvement in CTC solid-state electrolyte systems
- ✓ Development of a new family of alkaline salts to be expanded upon
- ✗ Remaining hardships to overcome (mechanical properties, conduction mechanism..)

➤ Perspectives of deeper CTC characterization and rationalization:


- solid-state NMR coupled to EPR spectroscopy
- DFT investigations
- $^6\text{Li}/^7\text{Li}$ isotopic labeling + TOF-SIMS spectrometry...



➤ Development of complete battery prototype with CTC single-ion electrolyte



THANK YOU!



Commissariat à l'énergie atomique et aux énergies alternatives
17 rue des Martyrs | 38054 Grenoble Cedex
www-liten.cea.fr

Établissement public à caractère industriel et commercial | RCS Paris B 775 685 019