



# Microstructural effect of p(O<sub>2</sub>) variation in mixed oxides (MOX) sintering

Gabriella Cunha Costa Miranda, Guillaume Bernard-Granger, Laure Ramond,  
Florent Lebreton, Abibatou Ndiaye, Thierry Gervais

## ► To cite this version:

Gabriella Cunha Costa Miranda, Guillaume Bernard-Granger, Laure Ramond, Florent Lebreton, Abibatou Ndiaye, et al.. Microstructural effect of p(O<sub>2</sub>) variation in mixed oxides (MOX) sintering. CIMTEC 2022 - 9th forum on new materials, Jun 2022, Montecatini Terme - Perugia, Italy. cea-04828185

HAL Id: cea-04828185

<https://cea.hal.science/cea-04828185v1>

Submitted on 9 Dec 2024

**HAL** is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

## **Microstructural Effect of p(O<sub>2</sub>) Variation in Mixed Oxides (MOX) Sintering**

FR-5 Nuclear fuel materials - Processing, microstructure, and properties relationship

**G.C.C. Miranda CEA/DES/ISEC/DMRC, Marcoule, F and Université Grenoble Alpes, Saint-Martin d'Hères, F**  
**G. Bernard-Granger, L. Ramond & F. Lebreton, CEA/DES/ISEC/DMRC, Université de Montpellier, Marcoule, F**  
**A. Ndiaye & T. Gervais, Orano Melox, Chusclan, F**

### **ABSTRACT (max 1300 characters)**

The atmosphere imposed during sintering of mixed oxide (MOX) pellets can influence the diffusion phenomena involved for densification, grain growth and to ensure chemical homogeneity.

In this work the microstructural effects of the sintering atmosphere p(O<sub>2</sub>) variation was studied for (U,Pu)O<sub>2±x</sub> containing 11 mol% of Pu/(U+Pu). Polished cross sections were characterized using electron probe microanalyses. They showed a chemical homogeneity of the material and the presence of a single phase for all the p(O<sub>2</sub>) values used.

With electron backscatter diffraction (EBSD) mappings, the average grain size measured by intercepts method showed an increase with the increase of p(O<sub>2</sub>). Following the same behavior, the distribution of grain size also presented a greater homogenization.

The pellets were at least 95% of the theoretical density (TD) with a good reproducibility in all atmospheres. However, the gradual decrease of the relative density with the increase of p(O<sub>2</sub>) indicates the existence of an optimum value of the (Density/Average grain size) couple.