



A plastic scintillator with enhanced Alpha-/Beta- PSD. Part I: Rationale and preparation

Matthieu Hamel, Krasimir Mitev

► To cite this version:

Matthieu Hamel, Krasimir Mitev. A plastic scintillator with enhanced Alpha-/Beta- PSD. Part I: Rationale and preparation. LSC 2020 - the 24th International Conference on Advances in Liquid Scintillation Spectrometry, Oct 2021, Shenzhen, China. cea-04892588

HAL Id: cea-04892588

<https://cea.hal.science/cea-04892588v1>

Submitted on 16 Jan 2025

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.



A Plastic Scintillator with enhanced Alpha-/Beta- PSD. Part I: Rationale and preparation


LSC 2020

Matthieu Hamel, Krasimir Mitev


Université Paris Saclay, CEA List, Palaiseau, FRANCE

Faculty of Physics, University of Sofia, Sofia, BULGARIA






Introduction



^{222}Rn detection with organic
scintillators




^{222}Rn detection with Pulse Shape
Discriminating plastics



Conclusions

A rather old scientific topic... but still hot!

Uraninite in a cloud chamber (C. Wilson, 1911)




Not exhaustive: semiconductors, ionization chambers, **scintillators**


Radiation detection with scintillators!

Definition

Material able to emit light upon interaction with radiation




SP33 plastic scintillator (Nuvia) exposed to $^{90}\text{Sr}/^{90}\text{Y}$ beta emitting source



Why new (plastic) scintillators?

Main motivation – Example for neutron detection



Goal of this lecture


To demonstrate that plastic scintillators can afford a suitable solution

→ Even for gas detection


Versatility of plastic scintillators

- Dimensions
- Scintillation properties
 - Time response (ns)
 - Wavelength (nm)
 - Yield (photons per deposited MeV, ph/MeV)
- Design for special applications
- **Cost**

Radon-222 detection with organic scintillators




Radon-222: decay




Radon-222 detection with organic scintillators


Radon-222: detection with organic scintillators




Electrostatic deposition on thin PS
Yamamoto, S. et al., IEEE Trans. Nucl. Sci. 46, 1929 (1999)



PS microspheres
Pelay, E. et al., J. Radioanal. Nucl. Chem. 314, 637 (2017)



Thin PS film for underwater ^{222}Rn measurement
Shitashima, K. et al., IEEE Sensors (2009)



Thin PS film for ^{222}Rn continuous monitoring in soil
Mitev, K. et al., IEEE NSS/MIC Conf. Rec. (2018)



Trans-stilbene (left) and EJ-276 (right) scintillators
Morishita, Y. et al., Nucl. Instr. Methods A 935, 207 (2019)



Radon-222 detection with Pulse Shape Discriminating plastics



Radon-222: main issues

- Gas
 - A specific detection strategy is mandatory
- Both alpha and beta emissions
 - Low linear energy transfers
 - Necessity to separate ^{222}Rn from progenies
 - Good alpha resolution (^{222}Rn vs. ^{218}Po decays: 5590 keV vs. 6002 keV)
 - Gamma background?

Solutions

- Use of Pulse Shape Discrimination between particles showing different dE/dx
- Diffusion of the gas within the volume of a plastic scintillator

Various dE/dx imply various photophysics

(1) Interaction of a beta

→ Excitation at the singlet state




Prompt fluorescence


(2) Interaction of an alpha

→ Excitation at the triplet state

→ Triplet-triplet annihilation



Delayed fluorescence




Problematic and Strategy

Hypothesis

It was assumed for a long time that plastic scintillators do not display n/γ pulse shape discrimination


No Triplet-Triplet Annihilation (TTA) → No delayed fluorescence

→ Improvements of triplets generation



Brownian motion of molecules in liquids

Random motion of particles suspended in a fluid



- First fluorophore
- Second fluorophore




Brownian motion does not exist in plastics!

Problematic and Strategy

Hypothesis

Pulse Shape Discrimination is possible when delayed fluorescence is observable



Embed efficient n/γ
discriminating systems
in **composite**
scintillators


Increase of
concentration of triplet
states

Triplet-harvesting
plastic scintillators

Problematic and Strategy

Hypothesis

Pulse Shape Discrimination is possible when delayed fluorescence is observable



Embed efficient n/γ
discriminating systems
**in composite
scintillators**

Increase of
concentration of triplet
states


Triplet-harvesting
plastic scintillators

Strategy: high concentration of primary fluorophore

Same strategy as for fast neutron/gamma discrimination which is well-documented

Primary fluorophore: biphenyl at content > 17 wt%

This high content allows triplet-triplet annihilation



- 1 Styrene – main component
- 2 1,4-butanediol dimethacrylate – cross-linker agent
- 3 Biphenyl – primary fluorophore
- 4 POPOP – wavelength shifter

→ A high content of ③ grants the n/γ discrimination

→ The high concentration of ③ requires the high concentration of ② as well (mechanical properties)


Strategy: high concentration of primary fluorophore

Same strategy as for fast neutron/gamma discrimination which is well-documented

Primary fluorophore: biphenyl at content > 17 wt%

This high content allows triplet-triplet annihilation

Fair to good isolation of ^{222}Rn against progenies




Conclusions

Following fast neutron/gamma discrimination development in plastic scintillators, analogy with alpha/beta discrimination can be performed

High quantity of biphenyl in a plastic scintillator leads to decent alpha/beta discrimination

Presentation of the results is ongoing with Dr. Mitev's talk

Some advertisement...



647 pages


15 chapters


1 appendix

1 index

36 authors

7 countries





THANK YOU!

Reviews, book and book section from our group:

Plastic scintillators: chemistry and applications, Springer-Nature, Cham, 2021.

Bertrand, G. H. V.; Hamel, M.; Sguerra, F. *Chem – Eur. J.* **2014**, 20, 15660-15685.

Bertrand, G. H. V.; Hamel, M.; Normand, S.; Sguerra, F. *Nucl. Instr. Methods A* **2015**, 776, 114-128.

Dumazert, J.; Coulon, R.; Lecomte, Q.; Bertrand, G. H. V.; Hamel, M. *Nucl. Instr. Methods A* **2018**, 882, 53-68.

Hamel, M.; Carrel, F. In *New Insights on Gamma Rays*; Maghraby, A., Ed.; InTech: 2017, p 47-66.